

Second edition
2022-09

Corrected version
2023-02

**Non-destructive testing of welds —
Radiographic testing —**

**Part 2:
X- and gamma-ray techniques with
digital detectors**

*Essais non destructifs des assemblages soudés — Contrôle par
radiographie —*

*Partie 2: Techniques par rayons X ou gamma à l'aide de détecteurs
numériques*

Document Preview

[ISO 17636-2:2022](https://standards.iteh.ai/catalog/standards/iso/fa562019-e6a0-4d60-be19-5f9ad56a21f1/iso-17636-2-2022)

<https://standards.iteh.ai/catalog/standards/iso/fa562019-e6a0-4d60-be19-5f9ad56a21f1/iso-17636-2-2022>



Reference number
ISO 17636-2:2022(E)

© ISO 2022

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 17636-2:2022

<https://standards.iteh.ai/catalog/standards/iso/fa562019-e6a0-4d60-be19-5f9ad56a21f1/iso-17636-2-2022>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	2
4 Symbols and abbreviated terms.....	6
5 Classification of radiographic techniques and compensation principles.....	8
5.1 Classification.....	8
5.2 Compensation principles, CP I, CP II or CP III.....	8
5.2.1 General.....	8
5.2.2 Compensation principle I (CP I).....	8
5.2.3 Compensation principle II (CP II).....	8
5.2.4 Compensation principle III (CP III).....	8
5.2.5 Theoretical background.....	9
6 General preparations and requirements.....	9
6.1 Protection against ionizing radiation.....	9
6.2 Surface preparation and stage of manufacture.....	9
6.3 Location of the weld in the radiograph.....	9
6.4 Identification of radiographs.....	9
6.5 Marking.....	9
6.6 Overlap of digital images.....	10
6.7 Types and positions of image quality indicators (IQIs).....	10
6.7.1 General.....	10
6.7.2 Duplex wire IQIs.....	10
6.7.3 Single wire or step-hole IQIs.....	10
6.8 Evaluation of image quality.....	11
6.9 Minimum image quality values.....	12
6.10 Personnel qualification.....	12
7 Recommended techniques.....	13
7.1 Test arrangements.....	13
7.1.1 General.....	13
7.1.2 Single-wall penetration of plane objects (see Figure 1).....	14
7.1.3 Single-wall penetration of curved objects with the source outside the object (see Figures 2 to 4).....	14
7.1.4 Single-wall penetration of curved objects with the source inside the object for panoramic exposure (see Figures 5 to 7).....	15
7.1.5 Single-wall penetration of curved objects with the source located off-centre and inside the object (see Figures 8 to 10).....	16
7.1.6 Double-wall penetration and double-image evaluation (DWDI) of pipes with the elliptic technique and the source and the detector outside the object (see Figure 11).....	17
7.1.7 Double-wall penetration and double-image evaluation (DWDI) with the perpendicular technique and source and detector outside the object (see Figure 12).....	17
7.1.8 Double-wall penetration and single-image evaluation (DWSI) of curved objects for evaluation of the wall next to the detector (see Figures 13 to 16).....	18
7.1.9 Penetration of objects with different material thicknesses (see Figure 17 to 19).....	19
7.2 Choice of tube voltage and radiation source.....	20
7.2.1 X-ray devices up to 1 000 kV.....	20
7.2.2 Other radiation sources.....	21
7.3 Detector systems and metal screens.....	22
7.3.1 Minimum normalized signal-to-noise ratio (SNR_N).....	22

7.3.2	Compensation principle II.....	25
7.3.3	Metal screens for IPs and shielding.....	25
7.4	Alignment of beam.....	25
7.5	Reduction of scattered radiation.....	26
7.5.1	Metal filters and collimators.....	26
7.5.2	Interception of backscattered radiation.....	26
7.6	Source-to-object distance.....	26
7.7	Geometric magnification technique.....	33
7.8	Maximum area for a single exposure.....	34
7.9	Processing.....	34
7.9.1	Scan and read-out of images.....	34
7.9.2	Correction of acquired DDA images.....	35
7.9.3	Bad pixel interpolation.....	35
7.9.4	Image processing.....	35
7.10	Monitor viewing conditions and storage of digital radiographs.....	36
8	Test report.....	36
Annex A (normative)	Number of exposures for acceptable testing of a circumferential butt weld.....	38
Annex B (normative)	Minimum image quality values.....	43
Annex C (normative)	Determination of basic spatial resolution.....	51
Annex D (informative)	Determination of minimum grey values for CR practice.....	53
Annex E (informative)	Grey values — General remarks.....	58
Annex F (informative)	Considering the detector unsharpness for f_{\min}.....	60
Annex G (informative)	Calculation of recommended X-ray tube voltages from Figure 20.....	63
Bibliography		64

ISO 17636-2:2022

<https://standards.iteh.ai/catalog/standards/iso/fa562019-e6a0-4d60-be19-5f9ad56a21f1/iso-17636-2-2022>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 5, *Testing and inspection of welds*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 17636-2:2013), which has been technically revised.

The main changes are as follows:

- the normative references have been updated;
- the figures have been updated;
- manual and automated inspection with DDAs has been considered in [6.6](#), [6.7](#), and [7.8](#);
- references to [Figures 1](#) to [19](#) have been updated throughout the document;
- in [6.7](#) a), the acceptance of a wire visibility shorter than 10 mm for pipes with an external diameter < 50 mm has been added;
- in [6.7.1](#), the use of ASTM wires and other IQIs by agreement of the contracting parties has been added;
- [6.8](#), “Evaluation of image quality” for digital radiography has been added;
- in [6.9](#) and [7.2.2](#), the lower thickness limit for Se-75 applications has been deleted;
- in [6.8](#), [6.9](#) and [7.3.1](#), a clarification for the IQI usage for DWDI technique has been added;
- permission to reduce SNR_N if the tube voltage is reduced or energy-resolving detectors are used to < 80 % of the values given in [Figure 20](#) has been added in [7.3.1](#);

ISO 17636-2:2022(E)

- in [7.3.2](#), the compensation principle II (CP II) has been extended to three wire pairs without the agreement of the contracting parties;
- [Annex C](#) has been shortened to avoid duplication with ISO 19232-5;
- in [D.2](#), a new note on fading has been added;
- a new [Annex F](#) has been added;
- a new [Annex G](#) has been added.

A list of all parts in the ISO 17636 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html. Official interpretations of ISO/TC 44 documents, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

This corrected version of ISO 17636-2:2022 incorporates the following corrections:

- the formulae in 3.11, 3.13, [Formula \(D.1\)](#) and [Figure D.2](#) have been updated to include units for the constant c ;
- [Formulae \(6\)](#) and [\(7\)](#) revised and D_d defined as "diagonal size of the detector area".

iTeh Standards (<https://standards.itih.ai>) Document Preview

ISO 17636-2:2022

<https://standards.itih.ai/catalog/standards/iso/fa562019-e6a0-4d60-be19-5f9ad56a21f1/iso-17636-2-2022>

Non-destructive testing of welds — Radiographic testing —

Part 2: X- and gamma-ray techniques with digital detectors

1 Scope

This document specifies techniques of digital radiography with the object of enabling satisfactory and repeatable results. The techniques are based on generally recognized practice and fundamental theory of the subject.

This document applies to the digital radiographic testing of fusion welded joints in metallic materials. It applies to the joints of plates and pipes. Besides its conventional meaning, “pipe”, as used in this document, covers other cylindrical bodies such as tubes, penstocks, boiler drums and pressure vessels.

This document specifies the requirements for digital radiographic X- and gamma-ray testing by either computed radiography (CR) or radiography with digital detector arrays (DDAs) of the welded joints of metallic plates and tubes for the detection of imperfections. It includes manual and automated inspection with DDAs.

Digital detectors provide a digital grey value image which can be viewed and evaluated using a computer ([Annex E](#)). This document specifies the recommended procedure for detector selection and radiographic practice. Selection of computer, software, monitor, printer and viewing conditions are important, but are not the main focus of this document. The procedure specified in this document provides the minimum requirements for radiographic practice which permits exposure and acquisition of digital radiographs with equivalent sensitivity for the detection of imperfections as film radiography (specified in ISO 17636-1).

This document does not specify acceptance levels for any of the indications found on the digital radiographs. ISO 10675 provides information on acceptance levels for weld inspection.

If contracting parties apply lower test criteria, it is possible that the quality achieved will be significantly lower than when this document is strictly applied.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5576, *Non-destructive testing — Industrial X-ray and gamma-ray radiology — Vocabulary*

ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel*

ISO 16371-1:2011, *Non-destructive testing — Industrial computed radiography with storage phosphor imaging plates — Part 1: Classification of systems*

ISO 19232-1, *Non-destructive testing — Image quality of radiographs — Part 1: Determination of the image quality value using wire-type image quality indicators*

ISO 19232-2, *Non-destructive testing — Image quality of radiographs — Part 2: Determination of the image quality value using step/hole-type image quality indicators*

ISO 19232-4, *Non-destructive testing — Image quality of radiographs — Part 4: Experimental evaluation of image quality values and image quality tables*