
**Timber structures — Finger-jointed
timber — Manufacturing and
production requirements**

*Structures en bois — Bois assemblé par entures multiples —
Exigences de fabrication et de production*

Sample Document

get full document from standards.iteh.ai



Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols	2
5 Conformance	3
5.1 Quality systems requirements	3
5.2 Manufacturing specifications	3
6 Requirements	3
6.1 Structural strength	3
6.1.1 Timber components	3
6.1.2 Grading methods	3
6.1.3 Finger-jointed timber	3
6.2 Adhesive	4
6.3 Finger joint glue bond integrity	4
6.4 Utility	4
6.5 Product identification	4
7 Verification	4
7.1 Structural strength	4
7.1.1 Qualification	4
7.1.2 Compliance testing	5
7.2 Adhesive	5
7.3 Finger-joint glue bond integrity	6
7.3.1 Verification at qualification	6
7.3.2 Verification for compliance testing	6
7.4 Utility requirements	6
7.5 Product identification requirements	6
Annex A (normative) Compliance (factory production control) testing — Strength verification of finger-jointed timber	7
Annex B (normative) Verification of the strength of finger-jointed timber by double-bending proof loading	9
Annex C (normative) Verification of the minimum strength of finger-jointed timber by tension proof loading	14
Annex D (normative) Verification of finger joint bond quality by assessment of wood fibre failure	16
Annex E (normative) Verification of finger joint bond quality by cyclic delamination	20
Annex F (normative) Verification of finger joint strength properties using the analytical method	22
Annex G (normative) Product identification	24
Annex H (informative) Basis of factor k_{ff}	25
Bibliography	26

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by ISO/TC 165, *Timber structures*.

get full document from standards.iteh.ai

Introduction

Finger-jointed timber is viewed as an alternative and substitute for sawn timber. Finger-jointed timber makes use of timber of various lengths and enables localized defects, particularly knots, to be docked out of otherwise high-quality sawn timber.

Qualification (initial type testing) and compliance (factory production control) testing are specified to assess if the components and manufacturing procedures used (finger joint profile, end pressure and other production variables) are appropriate for the characteristic values being claimed. A representative sample of the potential production is evaluated for tension and bending strength and finger joints are assessed for bond quality using delamination or wood fibre failure tests.

Sample Document

get full document from standards.iteh.ai

Sample Document

get full document from standards.iteh.ai

Timber structures — Finger-jointed timber — Manufacturing and production requirements

1 Scope

This document specifies the product and performance requirements for finger-jointed structural timber made from sawn timber elements.

The document does not cover products made using impressed (die-formed) joints or finger-jointed laminations for glued laminated timber, which is covered in ISO 12578.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9709, *Structural timber — Visual strength grading — Basic principles*

ISO 10983, *Timber — Finger joints — Minimum production requirements and testing methods*

ISO 12122-2, *Timber structures — Determination of characteristic values — Part 2: Sawn timber*

ISO 13910, *Timber structures — Strength graded timber — Test methods for structural properties*

ISO 13912, *Structural timber — Machine strength grading — Basic principles*

ISO 20152-1, *Timber structures — Bond performance of structural adhesives — Basic requirements*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

finger joint

end joint formed by machining a number of similar, tapered, symmetrical fingers in the ends of timber pieces that are then bonded together

3.2

finger-jointed timber

timber that contains two or more component pieces end-joined by *finger joints* (3.1)

Note 1 to entry: All pieces are of a single species or recognized species group, have the same nominal cross-section and the finger joints are formed using a common adhesive and production method.

3.3

production batch

finger-jointed timber (3.2) made during a continuous run on one production line

3.4

strength grade

population of timber having a set of structural properties and utility requirements

Note 1 to entry: Strength grade is defined in accordance with principles detailed with ISO 9709 (visual grading) or ISO 13912 (machine grading).

3.5

service class

service conditions to which *finger-jointed timber* (3.2) is subjected

Note 1 to entry: Service classes are defined in ISO 20152-1.

3.6

qualification

initial type testing

testing of *finger joints* (3.1) or *finger-jointed timber* (3.2) that is used to establish the statistical variables that describe the finger joint strength applicable to *strength grade* (3.4) and the parameters appropriate to the bond quality of the *service class* (3.5)

3.7

compliance

factory production control testing

process of demonstrating that *finger-jointed timber* (3.2) has strength values and bond quality of the specified *strength grade* (3.4) and *service class* (3.5)

3.8

standard length

length used in testing to determine characteristic values

Note 1 to entry: Standard lengths are defined in ISO 13910.

Note 2 to entry: Characteristic values are defined in ISO 12122-2

Note 3 to entry: Finger-jointed timber can be used as a substitute for sawn timber and therefore has its properties determined over the same test lengths.

4 Symbols

d	depth of finger-jointed timber in millimetres
b	width of finger-jointed timber in millimetres
$f_{k,m}$	characteristic strength in bending of a strength grade in megapascals
$f_{k,t}$	characteristic strength in tension of a strength grade in megapascals
$f_{k,m,verif} = k_{ff}f_{k,m}$	characteristic finger joint strength in bending of a single finger joint required for verification in megapascals
$f_{k,t,verif} = k_{ff}f_{k,t}$	characteristic finger joint strength in tension of a single finger joint required for verification in megapascals
k_{ff}	factor that allows for the effect of multiple finger joints in a standard length
L	standard test length for tension or bending as defined in ISO 13910 in millimetres
M	number of finger joints that occur in a standard length

NOTE Factor k_{ff} makes allowance for the negative impact of multiple finger joints on characteristic strengths and is used with the analytical method of assigning characteristic strengths. With the empirical method, the allowance is unnecessary.

5 Conformance

5.1 Quality systems requirements

Products conforming to this document shall be manufactured to a formalized manufacturing specification covering all relevant process variables under a quality system that includes

- in plant process control and internal auditing procedures, and
- auditing of plant process control and end-product quality.

5.2 Manufacturing specifications

The manufacturing specifications shall set the limits on all variables that affect or correlate with final product quality properties, including

- a) materials,
- b) glue bond quality,
- c) manufacturing process, and
- d) secondary processes and treatment, when applicable.

NOTE The above list is not necessarily exhaustive.

6 Requirements

6.1 Structural strength

6.1.1 Timber components

All timber components between finger joints shall have strength and stiffness characteristics of a declared strength grade. Where preservative or flame retardant treatment is used, the properties shall be determined after completion of the treatment.

6.1.2 Grading methods

All timber grading methods shall comply with the requirements of either ISO 9709 in the case of visual grading or ISO 13912 in the case of machine grading.

6.1.3 Finger-jointed timber

Bending and tension strengths are defined by reference to standard lengths defined in ISO 13910. Over these test lengths, finger-jointed timber shall have characteristic structural strengths in both bending and tension not less than the bending or tension strengths of the declared strength grade. The bending and tension strengths of the finger-jointed timber shall be determined during qualification and verified for each production batch except, if tension tests are omitted, then, in stress terms, the tension strength shall be deemed equal to 0,55 times the declared bending strength ($f_{k,t} = 0,55 f_{k,m}$).

NOTE 1 For verification of performance requirements in [6.1](#), refer to [7.1](#).