



**International
Standard**

ISO 1825

**Rubber hoses and hose assemblies
for aircraft ground fuelling and
defuelling — Specification**

*Tuyaux et flexibles en caoutchouc pour le ravitaillement
carburant et la vidange des avions au sol — Spécifications*

**Fifth edition
2026-02**

Sample Document

get full document from standards.iteh.ai

Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2026

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification	2
5 Service reeling diameter	3
6 Material and construction	3
6.1 Hoses.....	3
6.2 Hose assemblies.....	3
7 Dimensions and tolerances	4
7.1 Inside diameters.....	4
7.2 Thickness.....	4
7.3 Concentricity.....	4
7.4 Tolerances on length.....	4
7.5 Mass per unit length of hose.....	4
8 Physical properties	5
8.1 Rubber compounds.....	5
8.2 Finished hoses and hose assemblies.....	6
9 Electrical properties	7
9.1 Type B and type E (electrically bonded).....	7
9.2 Type C and type F (electrically conductive incorporating a semi-conductive cover compound).....	8
10 Frequency of testing	8
10.1 Hoses.....	8
10.2 Hose assemblies.....	8
11 Marking	8
11.1 Hoses.....	8
11.2 Hose assemblies.....	9
12 Test certificate or test report	9
13 Cleanliness	9
14 Protection for dispatch and storage	10
Annex A (normative) Method for determination of fuel-soluble matter	11
Annex B (normative) Method of test for cold embrittlement	12
Annex C (normative) Method for determination of adhesion between components	13
Annex D (normative) Method for determination of resistance to fuel contamination	14
Annex E (normative) Method of test for flexibility at 20 °C	15
Annex F (normative) Method of test for low temperature flexibility	16
Annex G (normative) Method of test for crush recovery	17
Annex H (normative) Method for determination of cyclic kinking resistance	19
Annex I (normative) Flammability test	20
Annex J (normative) Hydrostatic test	22
Annex K (normative) Method of test for vacuum resistance	23
Annex L (normative) Method of test for security of attachment of couplings	24

Annex M (normative) Type test and routine test	25
Annex N (informative) Recommended practice for hose flushing and handling	26
Bibliography	28

Sample Document

get full document from standards.iteh.ai

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Rubber and plastics hoses and hose assemblies*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 218, *Rubber and plastics hoses and hose assemblies*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fifth edition cancels and replaces the fourth edition (ISO 1825:2017), which has been technically revised.

The main changes compared to the previous edition are as follows:

- addition of two temperature classes (to bring the document in line with EI 1529);
- addition of nominal sizes 51 and 75;
- removal of the working pressure test in [Table 6](#) and [Annex J](#) (to bring the document in line with EI 1529);
- modification of the ozone resistance at 1 ppm instead of 0,5 ppm to align with EI 1529;
- removal of tests for production acceptance;
- revision of [Annexes F](#) and [G](#) (to bring the document in line with EI 1529);
- revision of the method specified in [Annex L](#).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Sample Document

get full document from standards.iteh.ai

Rubber hoses and hose assemblies for aircraft ground fuelling and defuelling — Specification

1 Scope

This document specifies the dimensions and construction of, and requirements for, four types of hose and hose assembly for use in all operations associated with the ground fuelling and defuelling of aircraft.

All four types are designed for:

- a) use with petroleum fuels having an aromatic-hydrocarbon content not exceeding 30 % by volume;
- b) operation within the temperature range of -30 °C to $+65\text{ °C}$ and such that they will be undamaged by climatic conditions of -40 °C to $+70\text{ °C}$ when stored in static conditions. For LT hose, the temperature range of -40 °C to $+65\text{ °C}$ and such that they will be undamaged by climatic conditions of -48 °C to $+70\text{ °C}$ when stored in static conditions;
- c) operation at up to 2,0 MPa (20 bar) maximum working pressure, including surges of pressure which the hose can be subjected to in service.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 188, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 1382, *Rubber — Vocabulary*

ISO 1402, *Rubber and plastics hoses and hose assemblies – Hydrostatic testing*

ISO 1817:2024, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids*

ISO 4649:2024, *Rubber, vulcanized or thermoplastic — Determination of abrasion resistance using a rotating cylindrical drum device*

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies*

ISO 6246, *Petroleum products — Gum content of fuels — Jet evaporation method*

ISO 7326, *Rubber and plastics hoses — Assessment of ozone resistance under static conditions*

ISO 7989-1, *Steel wire and wire products — Non-ferrous metallic coatings on steel wire — Part 1: General principles*

ISO 7989-2, *Steel wire and wire products — Non-ferrous metallic coatings on steel wire — Part 2: Zinc or zinc-alloy coating*

ISO 8031, *Rubber and plastics hoses and hose assemblies — Determination of electrical resistance and conductivity*

ISO 8033, *Rubber and plastics hoses — Determination of adhesion between components*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 10619-2:2021, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 2: Bending tests at sub-ambient temperatures*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1382 and ISO 8330 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

hose assembly

hose with either permanent or reusable end fittings attached

3.2

electrically bonded

hose or *hose assembly* (3.1) that uses a metallic wire connection to conduct static electricity

3.3

electrically conductive

hose or *hose assembly* (3.1) that is capable of conducting static electrical charges, using a conductive rubber layer

4 Classification

Hoses for this application are classified into four types and two grades according to their construction and electrical properties given in [Table 1](#). Each type of hose shall be divided into two temperature classes.

- Normal temperature class with an ambient working temperature of -30 °C to $+65\text{ °C}$.
- Low temperature class (LT) with an ambient working temperature of -40 °C to $+65\text{ °C}$.

Table 1 — Classification

Type	Grade	Construction
B	M	Electrically bonded, incorporating at least two low-resistance electrically conductive wires and a conductive cover compound.
C	Ω	Electrically conductive, incorporating a conductive cover compound.
E	M	Electrically bonded, incorporating at least one metallic wire helix, at least two low-resistance electrically conductive wires and a conductive cover compound. Has an enhanced defuelling capability.
F	Ω	Electrically conductive, incorporating at least one non-electrically conductive non-metallic helix and a conductive cover compound.

NOTE 1 Type C hoses are intended for general pressure applications on all vehicles used for plane fuelling. They can also be used for vehicle/rail car loading and discharge where excessive vacuum does not occur.

NOTE 2 Type F hoses can be used for plane delivery applications on vehicles that are also used for defuelling at high flow rates where type C hoses are not suitable.

NOTE 3 Type E and F hoses can also be used for vehicle/rail car loading and discharge, for trailer to fueller transfer and for elevation platform supply (riser) to provide greater kink resistance.

5 Service reeling diameter

Hoses shall be designed for operation on equipment fitted with hose reels of the diameters given in [Table 2](#).

These hoses remain substantially circular in cross-section when reeled on drums and should not be confused with hoses of the collapsible type that are intended to be reeled flat.

Table 2 — Service reeling diameters

Nominal size of hose	Minimum outside diameter of reeling drum used in service mm
19	225
25	300
31,5	375
32	375
38	450
50	550
51	550
63	600
75	600
76	600
100	900
101,5	900

6 Material and construction

6.1 Hoses

If the hose is mandrel-built and vulcanized on a mandrel, particulate-type release agents shall not be used. The hose shall be uniform in quality and be free from porosity, air holes, foreign inclusions and other defects when inspected visually.

The hose shall comprise the following components:

- a lining of synthetic rubber resistant to petroleum fuel;
- a reinforcement consisting of layers of woven, braided or spirally wound textile material;
- an outer cover made of synthetic rubber which shall be conductive and resistant to abrasion, outdoor exposure and petroleum fuel.

For types E and F hoses only, an embedded helix reinforcement shall be included in the construction. For type E hoses, the wire reinforcement used shall be a hard steel and shall have a galvanized finish in accordance with ISO 7989-1 and ISO 7989-2.

Types B and E shall also incorporate low-resistance electrically conductive wires to ensure that the hoses are electrically conductive.

The cover may have a shallow cloth-marked finish.

6.2 Hose assemblies

In order to produce the required electrical properties, the method of attachment of the couplings shall be in accordance with [Clause 9](#).