
**Polyethylene (PE) materials for piping
systems — Determination of Strain
Hardening Modulus in relation to slow
crack growth — Test method**

*Matériaux polyéthylène (PE) pour systèmes de canalisations —
Détermination du module d'écrouissage en relation avec la
propagation lente de fissures — Méthode d'essai*

Sample Document

get full document from standards.iteh.ai



Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	3
5 Apparatus	3
6 Test specimens	4
6.1 Test specimen geometry and dimensions	4
6.2 Test specimen preparation	4
7 Test procedure	5
8 Data analysis	6
9 Test report	6
Annex A (informative) Neo-Hookean constitutive model	8
Bibliography	10

Sample Document

get full document from standards.iteh.ai

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories* — *Test methods and basic specifications*.

Introduction

Resistance to slow crack growth is related in general to the lifetime of polyethylene and thus, the lifetime of polyethylene products, e.g. pipes and fittings. The slow crack growth behaviour can be regarded as a combination of yield stress and the capability of disentanglement of tie molecules as reported by Kramer and Brown.[3],[6],[7] The disentanglement capability of a polymer will determine its resistance against slow crack growth.

The strain hardening modulus of a polymer is a measure of the disentanglement capability of the tie molecules of this polymer and is an intrinsic property. The strain hardening modulus of polyethylene is obtained from a stress-strain curve above the natural draw ratio. The stress-strain curve of a compression moulded sample is relatively easily obtained using a tensile test apparatus equipped with an optical extensometer. The test time of the strain hardening modulus is a consequence of the speed of tensile testing and is therefore constant for all measurements and independent of the slow crack growth property of the tested material itself.

The strain hardening modulus value allows discrimination between materials. It has been demonstrated that the strain hardening modulus corresponds very well with several environmental stress cracking test methods for high density polyethylene.[4],[5],[8]

Sample Document

get full document from standards.iteh.ai