

---

---

**Diamond-like carbon films —  
Determination of friction and wear  
characteristics of diamond-like carbon  
films by ball-on-disc method**

*Revêtements de carbone amorphe — Détermination des  
caractéristiques de frottement et d'usure des revêtements de carbone  
amorphe par la méthode bille sur disque*

Sample Document

get full document from [standards.iteh.ai](https://standards.iteh.ai)



# Sample Document

get full document from [standards.iteh.ai](https://standards.iteh.ai)



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
[copyright@iso.org](mailto:copyright@iso.org)  
[www.iso.org](http://www.iso.org)

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Test materials and specimen preparation</b> .....	<b>2</b>
4.1 Materials.....	2
4.2 Ball specimen.....	2
4.3 Disc specimen.....	2
<b>5 Apparatus</b> .....	<b>3</b>
<b>6 Testing procedure</b> .....	<b>4</b>
6.1 Treatment of specimen before test.....	4
6.2 Preparation of wear test.....	4
6.3 Testing conditions for friction test.....	4
6.4 Testing conditions for friction and wear test.....	4
6.5 Measurement of friction force.....	4
6.6 Measurement of wear scar on ball specimen.....	5
6.7 Measurement of wear scar on disc specimen.....	5
6.8 Number of test repeats.....	5
<b>7 Calculation of test results</b> .....	<b>6</b>
7.1 Specific wear rate of diamond-like carbon films on ball specimen.....	6
7.2 Specific wear rate of diamond-like carbon films on disc specimen.....	6
7.3 Coefficient of friction.....	7
7.4 Rounding off of numerical values.....	7
<b>8 Test report</b> .....	<b>7</b>
<b>Annex A (informative) Uncertainty of measurement for calculating of coefficient of friction</b> .....	<b>9</b>
<b>Bibliography</b> .....	<b>12</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 107, *Metallic and other inorganic coatings*.

get full document from [standards.iteh.ai](http://standards.iteh.ai)

## Introduction

This International Standard gives guidance on conducting a sliding friction and wear test in a ball-on-disc configuration to determine the friction generated and wear observed in uniaxial sliding contacts between diamond-like carbon (DLC) films and a counter body.

The tribological properties of DLC films are different from those of metallic and ceramic coatings. DLC films have the tribological characteristics of low friction and low wear against other materials. Since a DLC film is a coating, rather than a bulk material, it has a limited amount of wear and possibility of delamination. Hence, a friction and wear testing method specific to DLC films is used to determine friction and wear resistance independent of delamination. In the ball-on-disk method using a DLC-coated ball on a non-coated disk, a non-coated ball on a DLC-coated disk, or a DLC-coated ball on a DLC-coated disk, the wear of DLC is minimal compared with other materials; for this reason, it is preferable to apply the coating on the ball to measure the wear rate with a reasonable accuracy. Of course, the wear on the ball side induces a decrease in contact pressure that must be taken into account for the friction coefficient interpretation. Because of these aspects, the ball-on-disk method is ideal for conventional testing of DLC coatings.

It should be noted that there are many parameters in the sliding contact that affect the magnitude of friction and wear. The aim of performing any wear test is to simulate, as closely as possible, the conditions that occur in the real application. As the deviation between the test conditions and the application conditions becomes larger, the test results become less relevant. To add credence to the test results, the appearance of the worn surfaces from the test samples are compared with the appearance of the worn surface from the actual worn component in order to ensure that similar wear mechanisms have taken place in each case. It is intended that the recommended test conditions suggested in this International Standard be used when the application conditions are not well defined but general comparison among materials is required.

This International Standard is useful for quality control of DLC films.

# Sample Document

get full document from [standards.iteh.ai](https://standards.iteh.ai)

# Diamond-like carbon films — Determination of friction and wear characteristics of diamond-like carbon films by ball-on-disc method

## 1 Scope

This International Standard specifies a procedure for and provides guidance on the determination of the coefficient of friction and the specific wear rate of diamond-like carbon (DLC) films. The method specifies that the materials are tested under dry conditions in pairs in a ball-on-disc configuration.

The results of the tests are not applicable when DLC-coated parts operate in a lubricated environment.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1101, *Geometrical product specifications (GPS) — Geometrical tolerancing — Tolerances of form, orientation, location and run-out*

ISO 3274, *Geometrical Product Specifications (GPS) — Surface texture: Profile method — Nominal characteristics of contact (stylus) instruments*

ISO 3290-1, *Rolling bearings — Balls — Part 1: Steel balls*

ISO 3290-2, *Rolling bearings — Balls — Part 2: Ceramic balls*

ISO 3611, *Geometrical product specifications (GPS) — Dimensional measuring equipment: Micrometers for external measurements — Design and metrological characteristics*

ISO 4287, *Geometrical Product Specifications (GPS) — Surface texture: Profile method — Terms, definitions and surface texture parameters*

ISO 13385-1, *Geometrical product specifications (GPS) — Dimensional measuring equipment — Part 1: Callipers; Design and metrological characteristics*

ISO 80000-1:2009, *Quantities and units — Part 1: General*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 3.1

#### **wear**

progressive mass removal from the surface of solid material due to relative motion with a contacting substance or substances

### 3.2

#### **wear test**

method of evaluating the friction and wear performance of materials in sliding contact