
**Fine ceramics (advanced ceramics,
advanced technical ceramics) —
Mechanical properties of ceramic
composites at ambient temperature
in air atmospheric pressure —
Determination of elastic properties by
ultrasonic technique**

Céramiques techniques (céramiques avancées, céramiques techniques avancées) — Propriétés mécaniques des céramiques composites à température ambiante sous air à pression atmosphérique — Détermination des propriétés élastiques par méthode ultrasonore



Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	5
5 Significance and use	6
6 Test equipment	7
6.1 Immersion tank with temperature measurement device	7
6.2 Holder of the probes and test object	7
6.3 Probes	7
6.4 Pulse generator	7
6.5 Signal display and recording system	7
7 Test object	7
8 Test object preparation	8
9 Test procedure	8
9.1 Choice of frequency	8
9.2 Establishment of the test temperature	9
9.3 Reference test without test object	9
9.4 Measurement with the test object	9
9.4.1 Determination of the bulk density and thickness	9
9.4.2 Mounting of the test object	9
9.4.3 Acquisition of different angles of incidence	9
10 Calculation	10
10.1 Delay	10
10.2 Calculation of the propagation velocities	10
10.3 Calculation of the refracted angle, θ_r	10
10.4 Identification of the elastic constants, C_{ij}	10
10.4.1 Basic considerations	10
10.4.2 Calculation of C_{33}	12
10.4.3 Calculation of C_{22} , C_{23} and C_{44}	12
10.4.4 Calculation of C_{11} , C_{13} and C_{55}	12
10.4.5 Calculation of C_{12} and C_{66}	12
10.5 Polar plots of the velocity curves	13
10.6 Calculation of the quadratic deviation and the confidence interval	14
10.7 Calculation of the engineering constants	14
11 Test validity	15
11.1 Measurements	15
11.2 Criterion of validity for the reliability of the C_{ij} components	15
12 Test report	15
Annex A (informative) Example of a presentation of the results for a material with orthotropic symmetry	17
Bibliography	19

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 206, *Fine ceramics*.

get full document from standards.iteh.ai

Fine ceramics (advanced ceramics, advanced technical ceramics) — Mechanical properties of ceramic composites at ambient temperature in air atmospheric pressure — Determination of elastic properties by ultrasonic technique

1 Scope

This document specifies an ultrasonic method to determine the components of the elasticity tensor of ceramic matrix composite materials at room temperature. Young's moduli shear moduli and Poisson coefficients, can be determined from the components of the elasticity tensor.

This document applies to ceramic matrix composites with a continuous fibre reinforcement: unidirectional (1D), bidirectional (2D), and tridirectional ($\times D$, with $2 < \times \leq 3$) which have at least orthotropic symmetry, and whose material symmetry axes are known.

This method is applicable only when the ultrasonic wavelength used is larger than the thickness of the representative elementary volume, thus imposing an upper limit to the frequency range of the transducers used.

NOTE Properties obtained by this method might not be comparable with moduli obtained by ISO 15733, ISO 20504 and EN 12289.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3611, *Geometrical product specifications (GPS) — Dimensional measuring equipment: Micrometers for external measurements — Design and metrological characteristics*

ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories*

EN 1389, *Advanced technical ceramics — Ceramic composites — Physical properties — Determination of density and apparent porosity*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in CEN/TR 13233 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1 stress-strain relations for orthotropic material

elastic anisotropic behaviour of a solid homogeneous body described by the elasticity tensor of fourth order C_{ijkl} , represented in the contracted notation by a symmetrical square matrix (6×6)

Note 1 to entry: If the material has at least orthotropic symmetry, its elastic behaviour is fully characterized by nine independent stiffness components C_{ij} , of the stiffness matrix (C_{ij}), which relates stresses to strains, or equivalently by nine independent compliance components S_{ij} of the compliance matrix (S_{ij}), which relates strains to stresses. The stiffness and compliance matrices are the inverse of each other.

If the reference coordinate system is chosen along the axes of symmetry, the stiffness matrix C_{ij} and the compliance matrix S_{ij} can be written as follows:

$$\begin{bmatrix} \sigma_1 \\ \sigma_2 \\ \sigma_3 \\ \sigma_4 \\ \sigma_5 \\ \sigma_6 \end{bmatrix} = \begin{bmatrix} C_{11} & C_{12} & C_{13} & 0 & 0 & 0 \\ C_{12} & C_{22} & C_{23} & 0 & 0 & 0 \\ C_{13} & C_{23} & C_{33} & 0 & 0 & 0 \\ 0 & 0 & 0 & C_{44} & 0 & 0 \\ 0 & 0 & 0 & 0 & C_{55} & 0 \\ 0 & 0 & 0 & 0 & 0 & C_{66} \end{bmatrix} \begin{bmatrix} \varepsilon_1 \\ \varepsilon_2 \\ \varepsilon_3 \\ \varepsilon_4 \\ \varepsilon_5 \\ \varepsilon_6 \end{bmatrix}$$

$$\begin{bmatrix} \varepsilon_1 \\ \varepsilon_2 \\ \varepsilon_3 \\ \varepsilon_4 \\ \varepsilon_5 \\ \varepsilon_6 \end{bmatrix} = \begin{bmatrix} S_{11} & S_{12} & S_{13} & 0 & 0 & 0 \\ S_{12} & S_{22} & S_{23} & 0 & 0 & 0 \\ S_{13} & S_{23} & S_{33} & 0 & 0 & 0 \\ 0 & 0 & 0 & S_{44} & 0 & 0 \\ 0 & 0 & 0 & 0 & S_{55} & 0 \\ 0 & 0 & 0 & 0 & 0 & S_{66} \end{bmatrix} \begin{bmatrix} \sigma_1 \\ \sigma_2 \\ \sigma_3 \\ \sigma_4 \\ \sigma_5 \\ \sigma_6 \end{bmatrix}$$

Note 2 to entry: For symmetries of higher level than the orthotropic symmetry, the C_{ij} and S_{ij} matrices have the same form as here above. Only the number of independent components reduces.

3.2 engineering constants

compliance matrix components of an orthotropic material which are in terms of engineering constants:

$$[S_{ij}] = \begin{bmatrix} 1/E_{11} & -\nu_{12}/E_{11} & -\nu_{13}/E_{11} & 0 & 0 & 0 \\ -\nu_{12}/E_{11} & 1/E_{22} & -\nu_{23}/E_{22} & 0 & 0 & 0 \\ -\nu_{13}/E_{11} & -\nu_{23}/E_{22} & 1/E_{33} & 0 & 0 & 0 \\ 0 & 0 & 0 & 1/G_{23} & 0 & 0 \\ 0 & 0 & 0 & 0 & 1/G_{13} & 0 \\ 0 & 0 & 0 & 0 & 0 & 1/G_{12} \end{bmatrix}$$

where

E_{11} , E_{22} and E_{33} are the elastic moduli in directions 1, 2 and 3, respectively;

G_{12} , G_{13} and G_{23} are the shear moduli in the corresponding planes;

ν_{12} , ν_{13} , ν_{23} are the respective Poisson coefficients.

3.3**angle of incidence** θ_i

angle between the direction 3 normal to the test specimen front face and the direction n_i of the incident wave

Note 1 to entry: See [Figures 1](#) and [2](#).

3.4**refracted angle** θ_r

angle between the direction 3 normal to the test specimen front face and the direction n of propagation of the wave inside the test specimen

Note 1 to entry: See [Figures 1](#) and [2](#).

3.5**azimuthal angle** ψ

angle between the plane of incidence ($3, n_i$) and plane $(2, 3)$ where n_i corresponds to the vector oriented along the incident plane wave and direction 2 corresponds to one of the axes of symmetry of the material

Note 1 to entry: See [Figure 1](#).




Figure 1 — Definition of angles