
**Rubber compounding ingredients —
Silica — Oil absorption of
precipitated silica**

*Ingrédients de mélange du caoutchouc — Silice — Absorption d'huile
des silices précipitées*

Sample Document

get full document from standards.iteh.ai



Reference number
ISO 19246:2016(E)

© ISO 2016

Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Principle	1
4 Materials	1
5 Equipment	2
6 Sampling	2
7 Procedure	2
7.1 Preliminary note.....	2
7.2 Determination.....	3
7.2.1 Method A (powder sample, micro-perls).....	3
7.2.2 Method B (granulated samples).....	4
7.3 Evaluation.....	4
7.3.1 Evaluation for powder and micro-perl materials.....	4
7.3.2 Evaluation of granulated materials.....	5
8 Precision data	5
9 Test report	5
Annex A (normative) Normalization of the mixer chamber by using reference materials	6
Annex B (informative) Precision data	12
Bibliography	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

get full document from standards.iteh.ai

Introduction

Due to health and environmental safety precautions, the determination of DOA absorption number has been worked out to substitute the determination of the DBP absorption number.

Dibutylphthalate (DBP) and dioctylphthalate (DOP) were commonly used in the past for determining the absorption capacity of pigments and extenders, like carbon black and silica. In the meantime, both substances have been banned as carcinogenic, mutagenic, reprotoxic substances (CMR) in different countries.

The search of a suitable alternative for DBP and DOP, especially for measuring the absorption capacity of polar pigments and extenders, like silica, calcium silicates and sodium aluminium silicates has been carried out in a task group of the Association of Synthetic Amorphous Silica Producers (ASASP) between 2004-2008. Out of different tested liquids, like linseed oil, paraffinic oil, etc., DOA was found as the most suitable alternative which leads to evaluated absorption numbers close to DBP measurement.

Sample Document

get full document from standards.iteh.ai

Sample Document

get full document from standards.iteh.ai

Rubber compounding ingredients — Silica — Oil absorption of precipitated silica

1 Scope

This International Standard specifies a general method for determining the liquid absorption capacity of a pigment and extender by using di-(2-ethylhexyl) adipate (DOA, CAS 103-23-1). The determination of the DOA absorption number is performed by means of an absorptometer which is equipped with a torque measurement and processing system. The DOA absorption number provides an indication of the void volume formed by the aggregates and agglomerates of the pigments and extenders.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 787-2, *General methods of test for pigments and extenders — Part 2: Determination of matter volatile at 105° C*

ISO 787-11, *General methods of test for pigments and extenders — Part 11: Determination of tamped volume and apparent density after tamping*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Principle

For the determination of the DOA absorption number, a defined amount of pigment or extender shall be transferred to the mixer chamber of the absorptometer.

Under permanent kneading, DOA shall be added with a constant rate. The indication is the torque of the kneaders. While the torque is low at the beginning, it increases rapidly near the point of liquid absorption of the sample and decreases after reaching the maximum torque. The mixture changes from a free-flowing state to one of a pasty consistency.

On basis of the raw data torque curve and the settings, a polynomial shall be calculated. The value for 70 % of the maximum torque of this third order polynomial (smoothed curve) shall be used for the evaluation of the DOA absorption number.

4 Materials

4.1 Di-(2-ethylhexyl)adipate (DOA), which density is approximately 0,925 5 g/cm³ at 20 °C and which refractive index $n_D(20\text{ °C})$ is approximately 1,447.

4.2 Pigment or extender, as powder or micro-perls.

It can be added directly to the absorptometer chamber. In case of testing granulated materials, the determination is performed using a granular size fraction of between 1,0 mm and 3,15 mm, that is received by pre-sieving.