
**Solar energy — Collector components
and materials —**

**Part 3:
Absorber surface durability**

Energie solaire — Composants et matériaux du collecteur —

Partie 3: Durabilité de la surface de l'absorbeur

Sample Document

get full document from standards.iteh.ai



Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Requirements and classification.....	2
5 Test methods for assessing material properties as measure of absorber performance.....	3
5.1 Sampling and preparation of test specimens.....	3
5.2 Sample conditioning.....	4
5.3 Solar absorptance.....	4
5.4 Thermal emittance.....	4
5.5 Adhesion.....	4
6 Tests for assessing the thermal stability of absorber surfaces.....	4
6.1 Principle.....	4
6.2 Apparatus.....	5
6.3 Procedure for execution of high temperature tests.....	6
6.4 Qualification procedure.....	7
7 Tests for determining the resistance to condensed water of absorber surfaces.....	7
7.1 Principle.....	7
7.2 Apparatus.....	8
7.3 Procedure for execution of constant condensation tests.....	9
7.4 Qualification procedure.....	10
8 Test for determining absorber surface corrosion resistance to high humidity air containing sulfur dioxide.....	10
8.1 Principle.....	10
8.2 Apparatus.....	11
8.3 Reference test specimen.....	12
8.4 Procedure for execution of corrosion test in high humidity air containing sulfur dioxide.....	12
8.5 Determination of shortest acceptable failure times in test by use of reference test specimens.....	13
8.6 Qualification procedure.....	13
9 Test report.....	14
Annex A (normative) Procedure for determination of solar absorption and thermal emittance of absorber surfaces.....	15
Annex B (normative) Temperature and failure time characteristics in assessment of thermal stability of absorber surface.....	19
Annex C (normative) Temperature/condensation and failure time characteristics together with qualification scheme in assessment of resistance to condensed water of absorber surface.....	25
Annex D (informative) Suitable designs for test apparatus to be used in the qualification testing of solar absorber surfaces.....	28
Bibliography.....	30

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 180, *Solar energy*.

ISO 22975 consists of the following parts, under the general title *Solar energy — Collector components and materials*:

— *Part 3: Absorber surface durability*

The following parts are under preparation:

— *Part 1: Evacuated tubes – Durability and performance*

— *Part 2: Heat-pipe for solar thermal application — Durability and performance*

Introduction

To effectively select, use and maintain a material in a given application, its degradation under service conditions must be predicted prior to use. Preferably, the durability of the material should be expressed quantitatively in terms of an expected service life. Durability in this case is the ability of a material to withstand deterioration caused by external factors in the environment, which may influence the performance of the material under service conditions. Service life is defined as the period of time after installation during which specific material properties important for the performance of the material meet or exceed minimum acceptable values.

The service life of a material is, thus, not solely dependent on its physical and chemical properties, but also on its performance requirement in the application considered, and on the external environmental factors, which influence performance under service conditions. In design work, the important question is if a specific material can be expected to have a service life longer than a certain value, the so-called design service life; the latter dictated by life cost considerations taking into account the total system. Service life assessment may be based on feed-back data from practice or on results from so-called qualification or acceptance durability tests.

The present recommended qualification procedure for solar absorber surface durability is based on the conduct of a series of short-term durability tests. During a test the optical performance of the absorber surface tested is determined by measuring its solar absorptance and thermal emittance. From the loss in optical performance of the absorber surface, its failure time in the test performed is assessed and compared with the shortest acceptable failure time set by the design service life of the absorber. Design service life, performance requirement defining failure time in terms of loss in optical performance, classification of type and levels of environmental stress are set under the assumption, that the absorber surface tested will be installed in a vented flat plate solar collector for use in domestic hot water systems and combisystems or under similar operating conditions.

The recommended qualification procedure may favourably be used in the development and validation of new kinds of absorber surfaces. From the results of tests, it can be concluded whether it is likely that an absorber surface tested may meet the requirement for an acceptable service life also in practice. The recommended durability testing procedure has proved to give results in fairly good agreement, both qualitatively and quantitatively, with what has actually been observed on absorber surfaces tested for longer time periods in solar collectors working under conditions corresponding to that in a typical domestic solar hot water system or combisystem. Nevertheless, if the tested absorber could not be qualified by present procedure, a more comprehensive investigation on durability is recommended and can still lead to a qualification.

The present procedure consists of three parts to test the absorber with respect to its stability against high temperature, against high humidity and condensation and against corrosion caused by atmospheric sulfur dioxide. The three parts are independent and can be assessed individually.

Sample Document

get full document from standards.iteh.ai

Solar energy — Collector components and materials —

Part 3: Absorber surface durability

1 Scope

This part of ISO 22975 is applicable to the determination of the long term behaviour and service life of selective solar absorbers for use in vented flat plate solar collectors working under conditions corresponding to that in a typical solar domestic hot water system or combisystem.

This part of ISO 22975 specifies a failure criterion of a solar absorber based on changes in optical performance of the absorber. The optical properties of interest are solar absorptance and thermal emittance.

This part of ISO 22975 specifies durability testing procedures focused on resistance to high temperatures and condensation of water on the absorber surface as well as high humidity in the presence of sulfur dioxide.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4624, *Paints and varnishes — Pull-off test for adhesion*

ISO 8407, *Corrosion of metals and alloys — Removal of corrosion products from corrosion test specimens*

ISO 9050, *Glass in building — Determination of light transmittance, solar direct transmittance, total solar energy transmittance, ultraviolet transmittance and related glazing factors*

ISO 10062, *Corrosion tests in artificial atmosphere at very low concentrations of polluting gas(es)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

design service life

time period of exposure under service conditions after installation during which the absorber surface is expected to meet the performance requirement

3.2

failure time

time period of exposure in the test at which the performance requirement limit is reached

3.3

solar absorptance, α_s

fraction of solar radiation energy absorbed by an absorber surface

3.4

thermal emittance, ε

ratio between the energy per unit area radiated by a surface at a given temperature and the corresponding energy radiated by a perfect black body at the same temperature

3.5

performance criterion function

PC

change in performance of an absorber surface in terms of changes in solar absorptance and thermal emittance

4 Requirements and classification

4.1 For classification of the durability of the absorber surface, the following performance requirement shall apply:

$$PC = -\Delta\alpha_s + 0,50\Delta\varepsilon \leq 0,05 \quad (1)$$

where

$\Delta\alpha_s$ is the change in the solar absorptance defined as

$$\Delta\alpha_s = \alpha_{s,t} - \alpha_{s,i} \quad (2)$$

with $\alpha_{s,t}$ equal to the value of the solar absorptance at the actual time of the test or at service, and

with $\alpha_{s,i}$ equal to the initial value of solar absorptance

where

$\Delta\varepsilon$ is the change in the thermal emittance

$$\Delta\varepsilon = \varepsilon_t - \varepsilon_i \quad (3)$$

with ε_t equal to the value of the thermal emittance at the actual time of the test or at service and

with ε_i equal to the initial value of thermal emittance.

NOTE 1 This performance criterion function is primarily based on location averaged values of the performance of typical solar domestic hot water systems and combisystems.[4] But, in the IEA Task 10 testing procedure referred to, a slightly different definition of PC is used, namely $PC = -\Delta\alpha_s - 0,25 \times \Delta\varepsilon$. Investigations made by the IEA MSTC group, however, showed that a weighting factor of 0,5 for the thermal emittance is more appropriate.[9]

NOTE 2 Higher values for the PC function may be used if considered more appropriate. $PC < 0,10$ should mean that the optical performance of absorber surface, and thus also the performance of solar domestic hot water system and combisystems, is allowed to be reduced to a level equal to 90 % of its original value during the design service life time period.[4]

4.2 Before durability testing of an absorber surface, all test specimens, sampled and prepared as specified in 5.1, shall be characterized with respect to their value for solar absorptance, determined as specified in 5.2, and their value for thermal emittance, determined as specified in 5.3.

To be qualified for testing, the set of test specimens shall have a standard deviation in the determined values for solar absorptance of less than 0,01 and for the determined values of thermal emittance a standard deviation less than 0,04.

4.3 For coated absorber surfaces, three extra test specimens shall be prepared and the adhesion of coating on those test specimens shall be assessed, as specified in [5.5](#).

For the absorber to be qualified for testing, the adhesion of coating shall be $> 0,15$ MPa for all test specimens (ISO 4624).

NOTE If considered accurate enough, the adhesion of the coating may be assessed by a more simple method. The method of ISO 2409[1] may be used and the requirement for satisfactory adhesion be set at the degree of 1. Alternatively, some suitable method in ISO 2819[2] may be used.

4.4 For an absorber surface to be qualified with respect to its thermal stability, the procedure of durability testing as specified in [Clause 6](#) shall be applied.

An absorber surface with sufficient thermal stability shall meet the requirement for test results as is specified in [6.4](#).

4.5 For an absorber surface to be qualified with respect to its resistance to condensed water when used in a non-airtight solar collector with more or less uncontrolled ventilation of air in the solar collector, the procedure of durability testing as specified in [Clause 7](#) shall be applied.

An absorber surface with sufficient resistance to condensed water shall meet the requirements for test results as are specified in [7.4](#).

4.6 If an absorber surface should be qualified with respect to its resistance to degradation caused by sulfur dioxide as an airborne pollutant, the procedure of durability testing as specified in [Clause 8](#) shall be applied (optionally).

An absorber surface may be qualified for use in two classes of solar collectors; the two classes representing different severity classes as regards atmospheric corrosivity.

Solar collector of type A: Airtight solar collector or solar collector with controlled ventilation of air in the space between the absorber surface and the cover plate. At the top and at the bottom of the frame of the solar collector, it should be equipped with ventilation holes. The atmospheric corrosivity at the bottom part of the solar collector under service conditions may typically correspond to a corrosion rate of zinc of $0,1 \text{ g/m}^2$ per year.

Solar collector of type B: Non-airtight solar collector with more or less uncontrolled ventilation of air in the solar collector. The atmospheric corrosivity at the bottom part of the solar collector under service conditions corresponds to a corrosion rate of zinc of $0,3 \text{ g/m}^2$ per year.

An absorber surface with sufficient resistance to degradation caused by sulfur dioxide in high humidity air, either regarding only a type A solar collector or regarding both type A and type B solar collectors, shall meet the requirements for test results as are specified in [8.6](#).

5 Test methods for assessing material properties as measure of absorber performance

5.1 Sampling and preparation of test specimens

For durability testing, test samples with an absorber surface area of preferably (50×50) mm shall be prepared. Sampling from larger pieces of absorber plate shall be made in such a way that variation in the optical properties between the different test specimens is minimized. Three extra test samples are also required for the assessment of the adhesion of the coating of un-aged test samples. For execution of the complete programme of durability tests of this recommended procedure, a minimum of 18 test samples are required.