
Rubber threads — Methods of test

Fils élastiques — Méthodes d'essai

Sample Document

get full document from standards.iteh.ai



Reference number
ISO 2321:2017(E)

© ISO 2017

Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Conditioning of samples or test pieces	3
5 Count	3
5.1 Sectional count	3
5.2 Conventional count (size number)	4
5.3 Apparatus	4
5.4 Procedure	5
5.4.1 Cutting out the test pieces	5
5.4.2 Weighing the test pieces	6
5.5 Expression of results	6
6 Metric yield	6
6.1 Procedure	6
6.2 Expression of results	7
7 Properties of rubber threads	7
8 Density	7
8.1 Principle	7
8.2 Method	8
8.2.1 Method A	8
8.2.2 Method B	8
9 Tensile strength, modulus and elongation at break	8
9.1 Apparatus	8
9.2 Procedure	9
9.2.1 Test piece preparation	9
9.2.2 Loop formation and testing	9
9.3 Expression of results	10
10 Schwartz value (SV)	10
10.1 Apparatus	10
10.2 Procedure	10
10.3 Expression of results	11
11 Elongation under a specified load	11
11.1 Test pieces	11
11.2 Apparatus	11
11.3 Procedure	12
11.4 Expression of results	12
12 Stress retention	13
12.1 Test pieces	13
12.2 Apparatus	13
12.3 Procedure	13
12.4 Expression of results	14
12.5 Test report	14
13 Tension set	14
13.1 Test piece preparation	14
13.2 Apparatus	15
13.3 Procedure	15
13.4 Expression of results	15
14 Accelerated ageing test on rubber threads in a relaxed state	16

14.1	General	16
14.2	Principle	16
14.3	Test pieces	16
14.4	Apparatus	16
14.5	Procedure	16
14.6	Expression of results	16
15	Dry-heat resistance	17
15.1	General	17
15.2	Principle	17
15.3	Apparatus	17
15.4	Procedure	18
15.5	Expression of results	18
15.6	Test report	18
16	Ribbons: Degree of adhesion between threads	19
16.1	General	19
16.2	Principle	19
16.3	Apparatus	19
16.4	Test pieces	19
16.5	Procedure	19
16.6	Expression of results	20
16.7	Test report	20
17	Resistance to copper staining during laundering	20
17.1	General	20
17.2	Principle	21
17.3	Reagents	21
17.4	Apparatus and materials	21
17.5	Test pieces	22
17.6	Preparation of test pieces	22
17.6.1	General	22
17.6.2	Individual samples of textile fabric	22
17.6.3	Individual textile yarns	22
17.6.4	Multifibre fabric swatches	22
17.7	Procedure	22
17.8	Test report	23
18	Effect of washing	23
18.1	General	23
18.2	Principle	23
18.3	Apparatus	23
18.4	Standard washing solution	24
18.5	Procedure	24
18.6	Expression of results	25
18.7	Test report	25
19	Resistance to atmospheric fume staining	25
19.1	General	25
19.2	Principle	26
19.2.1	General	26
19.2.2	Method A	26
19.2.3	Method B	26
19.3	Reagents	26
19.4	Apparatus and materials	26
19.4.1	Method A	26
19.4.2	Method B	26
19.5	Test pieces	28
19.5.1	General	28
19.5.2	Method A	28
19.5.3	Method B	28

19.6	Procedure	28
19.6.1	Method A	28
19.6.2	Method B	28
19.7	Test report	29
Bibliography		30

Sample Document

get full document from standards.iteh.ai

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 4, *Products (other than hoses)*.

This fourth edition cancels and replaces the third edition (ISO 2321:2006), which has been technically revised.

The main changes compared to the previous edition are as follows:

- [Clause 3](#) has been added to list all the terms and definitions;
- the distance between cutting blades in [Figure 1](#) has been added;
- the tensile testing of type A rings in [Figure 2](#) has been added and all the figure numbers have been updated;
- a new test, namely tension set, has been added in [Clause 13](#);
- the clause numbers in [Table 1](#) and [Table 2](#) have been updated;
- the unit of density has been changed from megagram per cubic metre (Mg/m³) to gram per cubic centimetre (g/cm³).

Rubber threads — Methods of test

1 Scope

This document specifies methods of test for determining general physical and mechanical properties of rubber threads, as well as specific mechanical properties of such threads in contact with fabrics. Owing to the comparatively small cross-section and the unusual conditions of service of this material, certain special methods have been developed.

Some of the tests included in this document are not entirely suitable for threads made from certain synthetic rubbers (e.g. urethane rubber). These tests are intended for natural or synthetic polyisoprene rubbers.

Comparisons can only be made on new rubber threads or on those with identical processing histories. In the interpretation of results from threads which have been subjected to spooling, fabrication or any other process, the previous history is important, and what is known of this and of any relaxation treatments used is intended to be reported.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 105-A03, *Textiles — Tests for colour fastness — Part A03: Grey scale for assessing staining*

ISO 188, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 1183-2, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

metric yield

unstretched length, in metres, of 1 000 g of the thread

3.2

density

<of thread> mass per unit volume of a test piece of thread measured at a standard laboratory temperature

Note 1 to entry: It is expressed in grams per cubic centimetre.

Note 2 to entry: The standard laboratory temperatures are given in ISO 23529.

3.3

tensile strength

stress at which the thread breaks when it is stretched under specified conditions, based on the initial cross-sectional area

Note 1 to entry: The value is expressed in megapascals ($1\text{MPa} = 1\text{N/mm}^2$).

3.4

modulus at 300 % and 500 %

stress calculated with respect to the original cross-sectional area, at 300 % and 500 % elongation

Note 1 to entry: It is measured in megapascals ($1\text{MPa} = 1\text{N/mm}^2$).

3.5

elongation at break

increase in length of the thread at break when it is stretched under the specified conditions, expressed as the percentage increase of the original length

EXAMPLE A test piece, 30 mm in length which increases in length to 210 mm at break, is said to give an elongation of 600 % at break.

3.6

Schwartz value

average of the stresses calculated with respect to the original cross-sectional area at a specified elongation measured on extension and retraction of a previously massaged (mechanically conditioned) thread

Note 1 to entry: It is expressed in megapascals ($1\text{MPa} = 1\text{N/mm}^2$).

Note 2 to entry: It is denoted by the abbreviated term, SV_n^c , where c is the massaging elongation (the elongation to which the test piece is stretched during mechanical conditioning) and n the elongation at which the readings are taken. Both c and n are expressed as percentages of the initial length as multiples of 100 and, unless otherwise specified, are chosen so that $c = n + 100$.

Note 3 to entry: The preferred values of n are 300 % and 500 %, depending on the type of thread under test.

3.7

Schwartz hysteresis ratio

ratio of the loads at a specified elongation measured on extension and retraction, after massaging (mechanical conditioning)

Note 1 to entry: It is denoted by the abbreviated term, SHR_n^c , where c is the massaging elongation (the elongation to which the test piece is stretched during mechanical conditioning) and n the elongation at which readings are taken. Both c and n are expressed as percentages of the initial length as multiples of 100 and, unless otherwise specified, are chosen so that $c = n + 100$.

Note 2 to entry: The preferred values of n are 300 % and 500 %, depending on the type of thread under test.

3.8**elongation under specified load**

percentage elongation of a rubber thread when stressed by the application of a specified load per unit area

Note 1 to entry: It is determined by applying a load to an unmassaged thread (i.e. a thread which has not been mechanically conditioned) and so is liable to be affected by the age and previous history (including storage history and any conditioning) of the thread.

Note 2 to entry: It is normally determined at two levels of applied force: 15,5 kPa (= 15,5 mN/mm²) and 27,4 kPa (= 27,4 mN/mm²).

3.9**stress retention**

residual load, expressed as a percentage of the original load on the thread, after the test piece has been maintained at a constant elongation (usually 100 %) for a specified time

3.10**tension set**

elongation remaining in a test piece in the relaxed condition after it has been subjected to a constant elongation at a specified time, expressed as a percentage of the elongation

3.11**discoloration**

change in the original shade of a product, resulting from outside influences

3.12**colour staining**

undesired pick-up of colour by a fabric

- a) when immersed in water, dry-cleaning solvent or a similar liquid medium, which contains dyestuffs or colouring material not intended for colouring the fabric;
- b) by direct contact with other dyed material from which colour is transferred by bleeding or sublimation

4 Conditioning of samples or test pieces

The samples or test pieces shall be kept in a relaxed state in one of the standard atmospheres described in ISO 23529, for not less than 16 h before testing. The tests shall be carried out under similar atmospheric conditions. The test piece selected shall be clean, dry and free from any visual defects. Samples or test pieces shall not be allowed to come into contact with copper or manganese or their compounds during conditioning or testing.

5 Count**5.1 Sectional count**

The sectional count of a rubber thread is given by the value of its cross-sectional area, expressed in square millimetres.

The sectional count corresponds to the tex count for a nominal density of 1 g/cm³. The use of the sectional count is recommended.