
**Plastics — Polyols for use in the
production of polyurethanes —
Determination of basicity (total amine
value), expressed as percent nitrogen**

*Plastiques — Polyalcools utilisés pour la production de
polyuréthannes — Détermination de la basicité (valeur totale
d'amines) en pourcentage d'azote*

Sample Document

get full document from standards.iteh.ai



Reference number
ISO 25761:2014(E)

© ISO 2014

Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	2
5 Sampling.....	2
6 Apparatus.....	2
7 Interference.....	2
8 Reagents.....	2
9 Procedure.....	3
10 Expression of results.....	4
11 Precision and bias.....	4
11.1 General.....	4
11.2 Precision.....	5
11.3 Bias.....	5
12 Test report.....	5
Annex A (informative) Determination of the factor F for 0,1 mol/l perchloric acid in acetic acid.....	6
Bibliography.....	7

get full document from standards.iteh.ai

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information.

The committee responsible for this document is ISO/TC 61, *Plastics*, Subcommittee SC 12, *Thermosetting materials*.

This second edition cancels and replaces the first edition (ISO 25761:2008), which has been technically revised.

Introduction

Polyurethanes are produced by the catalysed reaction of isocyanates with polyols. The basicity of the polyol employed affects the rate of reaction and speed of cure of the product. It is therefore necessary to determine the basicity in order to predict reactivity and monitor product quality.

Sample Document

get full document from standards.iteh.ai