
**Clear liquids — Estimation of colour
by the Gardner colour scale**

*Liquides clairs — Évaluation de la couleur au moyen de l'échelle de
couleur Gardner*

Sample Document

get full document from standards.iteh.ai



Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus and materials	1
5 Sampling	2
6 Procedure	2
7 Expression of results	2
8 Precision	2
8.1 General.....	2
8.2 Repeatability limit, <i>r</i>	2
8.3 Reproducibility limit, <i>R</i>	3
8.4 Bias.....	3
9 Test report	3
Annex A (normative) Gardner colour standards	4
Bibliography	6

Sample Document

get full document from standards.iteh.ai

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

ISO 4630 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 10, *Test methods for binders for paints and varnishes*, in collaboration with ASTM D 01.34, *Naval stores*. It has been harmonized with ASTM D 1544-04, *Standard test Method for Color of Transparent Liquids (Gardner Color Scale)* and ASTM D 6166-12, *Standard Test Method for Color of Naval Stores and Related Products (Instrumental Determination of Gardner Color)*.

This third edition of ISO 4630 cancels and replaces ISO 4630-1:2004 and ISO 4630-2:2004, which have been technically revised. The main changes are:

- a) both standards have been combined into one standard;
- b) the spectrophotometric method (formerly described in ISO 4630-2:2004) is the only one standardized now;
- c) the original visual comparison of colours (formerly described in ISO 4630-1:2004) has been deleted, and the description of manufacture of the original Gardner colour standards has been moved to [Annex A](#).

Clear liquids — Estimation of colour by the Gardner colour scale

1 Scope

This International Standard specifies a method for estimating the colour of optically clear, yellow/brownish coloured liquid products by means of the Gardner colour scale using colour-measuring instruments. The method uses the Gardner colour scale described in [Annex A](#).

It is applicable to drying oils, varnishes and solutions of fatty acids, polymerized fatty acids, resins, tall oil, tall oil fatty acids, rosin and related products. The results might be invalid if other products are tested.

The method described provides a more precise way of measuring Gardner colour than a visual sample comparison using human eyes. It is applicable to products having colours from Gardner 1 to Gardner 18. The Gardner scale is not applicable to products with colours darker than 18. For products with colours lighter than Gardner 1 the method specified in ISO 6271 applies.

2 Normative references

The following referenced documents, in whole or in part, are normally referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 5725-2, *Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method*

ISO 13632, *Binders for paints and varnishes — Rosin — Sampling and sample preparation for colour measurement*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

CIE Publication No. 15:2004, *Colorimetry*

3 Principle

The colour of a liquid sample is measured using an instrument capable of measuring transmitted colour and reporting in Gardner colours or in a colour system that can be converted into Gardner colours.

4 Apparatus and materials

4.1 Colour-measuring instrument, spectrophotometer capable of measuring transmitted colour ($0^\circ/180^\circ$ geometry) and reporting the results in the Gardner colour scale. If such an instrument is not available, one may be used which is capable of measuring transmitted colour and reporting in tristimulus values using standard illuminant C and the 2° observer, described in CIE Publication No. 15:2004.

4.2 Absorption cells, 10 mm light path length recommended, unless a different path length is specified by the instrument manufacturer or

4.3 Glass tubes, 11 mm path length. Glass test tubes designed for a specific instrument may be used.