
**Styrene-butadiene rubber (carbon
black or carbon black and oil
masterbatches) — Evaluation
procedure**

*Caoutchouc butadiène-styrène (mélanges-mâtres avec du noir
de carbone ou avec du noir de carbone et de l'huile) — Méthode
d'évaluation*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 4659:2020

<https://standards.iteh.ai/catalog/standards/iso/e53f3bbd-3701-4ac4-bf80-e1b9c38eddd7/iso-4659-2020>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 4659:2020

<https://standards.iteh.ai/catalog/standards/iso/e53f3bbd-3701-4ac4-bf80-e1b9c38eddd7/iso-4659-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Sampling and further preparative procedures	2
5 Physical and chemical tests on raw rubber	2
5.1 Mooney viscosity	2
5.2 Volatile matter	2
5.3 Ash	2
6 Preparation of test mixes for evaluation	2
6.1 Standard test formulation	2
6.2 Procedure	2
6.2.1 Equipment and procedure	2
6.2.2 Mixing procedure	3
7 Evaluation of vulcanization characteristics by a curemeter test	5
7.1 Using an oscillating-disc curemeter	5
7.2 Using a rotorless curemeter	5
8 Evaluation of tensile stress-strain properties of vulcanized test mixes	6
9 Precision	6
10 Test report	6
Annex A (informative) Precision	8
Bibliography	10

ISO 4659:2020

<https://standards.iteh.ai/catalog/standards/iso/e53f3bbd-3701-4ac4-bf80-e1b9c38eddd7/iso-4659-2020>