International Standard

ISO 4892-1

Plastics — Methods of exposure to laboratory light sources —

Part 1: General guidance and requirements

Plastiques — Méthodes d'exposition à des sources lumineuses de laboratoire —

Partie 1: Lignes directrices générales et exigences

Fourth edition
2024-10

Corrected version
2026-02

Sample Document
get full document from standards.iteh.ai

Reference number
ISO 4892-1:2024(en)

© ISO 2024

Sample Document

get full document from standards.iteh.ai

COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

ISO 4892-1:2024 • https://standards.iteh.ai/catalog/standards/iso/ec6eb76c-899c-432a-8c79-32f4135c8a2c/iso-4892-1-2024

Contents

Page

Foreword ... **iv**

Introduction ... **vi**

1 Scope ... **1**

2 Normative references ... **1**

3 Terms and definitions ... **1**

4 Principle ... **3**
4.1 General ... 3
4.2 Significance ... 3
4.3 Use of accelerated tests with laboratory light sources ... 5

5 Requirements for laboratory exposure devices ... **6**
5.1 Irradiance ... 6
5.2 Temperature ... 7
5.3 Humidity and wetting ... 10
5.4 Other requirements for the exposure device ... 11

6 Test specimens ... **11**
6.1 Form, shape and preparation ... 11
6.2 Number of test specimens ... 12
6.3 Storage and conditioning ... 12

7 Test conditions and procedure ... **13**
7.1 Set points for exposure conditions ... 13
7.2 Property measurements on test specimens ... 14
7.3 Sampling for intermediate and final evaluation ... 14

8 Periods of exposure and evaluation of test results ... **14**
8.1 General ... 14
8.2 Use of control materials ... 14
8.3 Use of results in specifications ... 15

9 Test report ... **15**

Annex A (normative) **Procedures for measuring the irradiance uniformity in the specimen exposure area** ... **18**

Annex B (informative) **Factors that decrease the degree of correlation between artificial accelerated weathering or artificial accelerated irradiation exposures and actual-use exposures** ... **21**

Annex C (informative) **Solar spectral irradiance standards** ... **24**

Bibliography ... **27**

Sample Document
Full document from standards.iteh.ai

© ISO 2024 – All rights reserved

ISO 4892-1:2024 • https://standards.iteh.ai/catalog/standards/iso/ec6eb76c-899c-432a-8c79-32f4135c8a2c/iso-4892-1-2024

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

Sample Document

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 6, *Ageing, chemical and environmental resistance*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

get full document from standards.iteh.ai

This fourth edition cancels and replaces the third edition (ISO 4892-1:2016), which has been technically revised.

The main changes are as follows:

— the definition of file specimen (see 3.2) and weathering reference material (see 3.5) have been clarified and Notes to entry have been added;

— definition and Notes to entry of artificial accelerated weathering (see 3.3) and artificial accelerated irradiation (see 3.4) have been clarified;

— new terms, definitions and Notes to entry have been added for black-panel thermometer (see 3.7), black-standard thermometer (see 3.8), white-panel thermometer (see 3.9), and white-standard thermometer (see 3.10);

— reference to ISO/TR 18486 has been added under 4.2.4;

— calibration requirements have been clarified in 5.1.7, 5.2.8, 5.2.9, 5.3.6;

— requirements regarding black-panel thermometer, black-standard thermometer, white-panel thermometer, and white-standard thermometer in 5.2 and Table 2 have been clarified;

— reference to ISO 23741 has been added in 5.3.1;

— new subclause 7.3 “Sampling for intermediate and final evaluation” has been added;

— requirements for the test report have been updated;

— reference to CIE 85 in Annex C has been updated to CIE 241.

© ISO 2024 – All rights reserved

ISO 4892-1:2024 • https://standards.iteh.ai/catalog/standards/iso/ec6eb76c-899c-432a-8c79-32f4135c8a2c/iso-4892-1-2024

A list of all parts in the ISO 4892 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This corrected version of ISO 4892-1:2024 incorporates the following corrections:

— in 6.1.3, information on test specimens have been corrected.

Sample Document

get full document from standards.iteh.ai

© ISO 2024 – All rights reserved

ISO 4892-1:2024 • https://standards.iteh.ai/catalog/standards/iso/ec6eb76c-899c-432a-8c79-32f4135c8a2c/iso-4892-1-2024

Introduction

Plastics are often used outdoors or in indoor locations where they are exposed to solar radiation or to window-glass-filtered solar radiation for long periods. It is therefore very important to determine the effects of solar radiation, heat, moisture and other climatic stresses on the colour and other properties of plastics. Outdoor exposures to solar radiation and to solar radiation filtered by window glass are described in ISO 877 (all parts)[1]. However, it is often necessary to rapidly determine the effects of radiation, heat and moisture on the physical, chemical and optical properties of plastics with artificial accelerated weathering or artificial accelerated irradiation exposures that use specific laboratory light sources. Exposures in these laboratory devices are conducted under more controlled conditions than found in natural environments and are intended to accelerate eventual polymer degradation and product failures.

Relating results from accelerated weathering or artificial accelerated irradiation exposures to those obtained in actual-use conditions is difficult because of variability in both types of exposure and because laboratory tests never reproduce exactly all the exposure stresses experienced by plastics exposed in actual-use conditions. No single laboratory exposure test can be specified as a total simulation of actual-use exposures.

The relative durability of materials in actual-use exposures can be very different depending on the location of the exposure because of differences in UV radiation, time of wetness, temperature, pollutants and other factors. Therefore, even if results from specific accelerated weathering or artificial accelerated irradiation exposures are found to be useful for comparing the relative durability of materials exposed in a particular outdoor location or in particular actual-use conditions, it cannot be assumed that they will be useful for determining the relative durability of materials exposed in a different outdoor location or in different actual-use conditions.

Sample Document

get full document from standards.iteh.ai

© ISO 2024 – All rights reserved

ISO 4892-1:2024 • https://standards.iteh.ai/catalog/standards/iso/ec6eb76c-899c-432a-8c79-32f4135c8a2c/iso-4892-1-2024

Plastics — Methods of exposure to laboratory light sources —

Part 1: General guidance and requirements

1 Scope

This document provides general guidance and requirements relevant to the selection and operation of the methods of exposure described in detail in subsequent parts of the ISO 4892 series. It also specifies general performance requirements for devices used for exposing plastics to laboratory light sources. Information regarding performance requirements is for producers of artificial accelerated weathering or artificial accelerated irradiation devices.

This document also provides information on the interpretation of data from artificial accelerated weathering or artificial accelerated irradiation exposures. More specific information about methods for determining the change in the properties of plastics after exposure and reporting these results is not part of this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

Sample Document
get full document from standards.iteh.ai

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 4582, *Plastics — Determination of changes in colour and variations in properties after exposure to glass-filtered solar radiation, natural weathering or laboratory radiation sources*

ISO 4892-2, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps*

ISO 4892-3, *Plastics — Methods of exposure to laboratory light sources — Part 3: Fluorescent UV lamps*

ISO 4892-4, *Plastics — Methods of exposure to laboratory light sources — Part 4: Open-flame carbon-arc lamps*

ISO 9370, *Plastics — Instrumental determination of radiant exposure in weathering tests — General guidance and basic test method*

ASTM G113, *Standard terminology relating to natural and artificial weathering tests of nonmetallic materials*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ASTM G113 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at https://www.electropedia.org/

© ISO 2024 – All rights reserved

ISO 4892-1:2024 • https://standards.iteh.ai/catalog/standards/iso/ec6eb76c-899c-432a-8c79-32f4135c8a2c/iso-4892-1-2024

3.1
control material
<weathering testing> material which is of similar composition and construction to the test material and which is exposed at the same time for comparison with the test material

Note 1 to entry: An example of the use of a control material would be when a formulation different from one currently being used is being evaluated. In that case, the control material would be the plastic made with the original formulation.

Note 2 to entry: A control material is sometimes referred to as control.

3.2
file specimen
portion of the material to be tested which is stored under conditions likely to cause minimal material degradation

Note 1 to entry: These are typically dark, dry and temperate conditions.

Note 2 to entry: The file specimen is used for comparison between the exposed and unexposed states.

3.3
artificial accelerated weathering
exposure of a material in a laboratory device intended to simulate outdoor ageing faster by radiation, temperature, and moisture, typically including liquid water

Note 1 to entry: These exposures are typically using a laboratory light source intended to simulate outdoor conditions in an attempt to produce more rapidly the same changes that occur when the material is used in an outdoor environment.

Note 2 to entry: The conditions can be cyclic and intensified compared with those encountered in outdoor exposure.

Sample Document

Note 3 to entry: The device can include means for control and/or monitoring of the light source and other weathering parameters. It may also include exposure to special conditions, such as acid spray to simulate the effect of air pollution.

3.4
artificial accelerated irradiation
Get full document from standards.iteh.ai
exposure of a material to a light source in a laboratory device intended to simulate ageing faster by radiation, temperature, and moisture, typically only in the form of relative humidity, but without liquid water

Note 1 to entry: These exposures are typically using a laboratory light source intended to simulate window-glass-filtered solar radiation or radiation from interior lighting sources in an attempt to produce more rapidly the same changes that occur when the material is used in an indoor environment.

Note 2 to entry: These exposures are commonly referred to as fading or lightfastness tests.

3.5
weathering reference material
material of known performance when exposed to solar radiation, heat and moisture

Note 1 to entry: Weathering reference materials are used for weathering and irradiation testing.

3.6
reference specimen
portion of the weathering reference material that is to be exposed

3.7
black-panel thermometer
BPT
flat, black coated metal plate which is exposed to radiation, with a temperature sensor attached to the front centre of the exposed surface

Note 1 to entry: The intention is to mimic the thermal conditions of a coated black metal panel. The measured temperature depends on heat fluxes by short and long wavelength radiation and convection on the front side and the rear side of the panel.

© ISO 2024 – All rights reserved

ISO 4892-1:2024 • https://standards.iteh.ai/catalog/standards/iso/ec6eb76c-899c-432a-8c79-32f4135c8a2c/iso-4892-1-2024

Note 2 to entry: The BPT provides a measure for the reference surface temperature of irradiated surfaces. The BPT will typically show lower temperatures than the black-standard thermometer under the same conditions.

Note 3 to entry: Black-panel thermometers are sometimes referred to as uninsulated black-panel thermometers.

3.8
black-standard thermometer
BST
flat, black coated metal plate which is exposed to radiation, with a thermal insulation on the backside and the temperature sensor is attached to the rear centre of the exposed plate and between metal plate and insulation

Note 1 to entry: The intention is to mimic the thermal conditions of a common black polymer specimen. The measured temperature depends on heat fluxes by short and long wavelength radiation and convection on the frontside of the panel only.

Note 2 to entry: The BST will show one of the highest temperatures in the specimen plane.

Note 3 to entry: Black-standard thermometers are sometimes referred to as insulated black-panel thermometers.

3.9
white-panel thermometer
WPT
flat, white coated metal plate which is exposed to radiation, with a temperature sensor attached to the front centre of the exposed surface

Note 1 to entry: The intention is to mimic the thermal conditions of a coated white metal panel. The measured temperature depends on heat fluxes by short and long wavelength radiation and convection on the front side and the rear side of the panel.

Sample Document

Note 2 to entry: The WPT provides a measure for the reference surface temperature of irradiated surfaces. The WPT will typically show lower temperatures than the white-standard thermometer.

3.10
white-standard thermometer
WST
flat, white coated metal plate which is exposed to radiation, with a thermal insulation on the backside and the temperature sensor is attached to the rear centre of the exposed plate and between metal plate and insulation

get full document from standards.iteh.ai

Note 1 to entry: The intention is to mimic the thermal conditions of a common white polymer specimen. The measured temperature depends on heat fluxes by short and long wave radiation and convection on the frontside of the panel only.

4 Principle

4.1 General

Specimens of the samples to be tested are exposed to laboratory light sources under controlled environmental conditions. The methods described include the requirements which shall be met for the measurement of the irradiance and radiant exposure in the plane of the specimen, the temperature of specified white and black surface thermometers, the chamber air temperature and the relative humidity.

NOTE In this document, the term “light source” refers to radiation sources that emit UV radiation, visible radiation, infrared radiation or any combination of these types of radiation.

4.2 Significance

4.2.1 When conducting exposures in devices that use laboratory light sources, it is important to consider how well the accelerated-test conditions simulate the actual-use environment for the plastic being tested. In addition, it is essential to consider the effects of variability in both the accelerated test and actual exposures

© ISO 2024 – All rights reserved

ISO 4892-1:2024 • https://standards.iteh.ai/catalog/standards/iso/ec6eb76c-899c-432a-8c79-32f4135c8a2c/iso-4892-1-2024