
**Wrought aluminium and aluminium
alloys — Sheets, strips and plates —**

**Part 3:
Strips: Tolerances on shape and
dimensions**

*Aluminium et alliages d'aluminium corroyés — Tôles, bandes et tôles
épaisses —*

Partie 3: Bandes: Tolérances sur forme et dimensions

Sample Document

get full document from standards.iteh.ai



Reference number
ISO 6361-3:2014(E)

© ISO 2014

Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents		Page
Foreword		iv
1	Scope	1
2	Dimensional tolerances	1
2.1	Thickness	1
2.2	Width	3
3	Shape tolerances	3
Bibliography		5

Sample Document

get full document from standards.iteh.ai

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information.

The committee responsible for this document is ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 6, *Wrought aluminium and aluminium alloys*.

This third edition cancels and replaces the second edition (ISO 6361-3:2011), which has been technically revised.

ISO 6361 consists of the following parts, under the general title *Wrought aluminium and aluminium alloys — Sheets, strips and plates*:

- *Part 1: Technical conditions for inspection and delivery*
- *Part 2: Mechanical properties*
- *Part 3: Strips: Tolerances on shape and dimensions*
- *Part 4: Sheets and plates: Tolerances on shape and dimensions*
- *Part 5: Chemical composition*

Wrought aluminium and aluminium alloys — Sheets, strips and plates —

Part 3: Strips: Tolerances on shape and dimensions

1 Scope

This part of ISO 6361 specifies the tolerances on shape and dimensions for wrought aluminium and aluminium alloy strip by cold-rolling for general engineering applications.

It applies to products with thickness of over 0,15 mm up to, and including 16 mm.

It does not apply to semi-finished rolled products in coiled form to be subjected to further rolling (reroll stock), or to special products such as those that are corrugated or embossed.

Technical conditions for inspection and delivery of products covered by this part of ISO 6361 are specified in ISO 6361-1.

2 Dimensional tolerances

2.1 Thickness

Thickness tolerances shall be in accordance with [Tables 1](#) and [2](#).

When the tolerance is specified as either all plus, or minus side, the value in [Table 1](#), or in [Table 2](#), shall be doubled.

Tolerances for the products exceeding the range of specified thickness and width shall be agreed upon by the purchaser and the supplier.

Table 1 — Thickness tolerances

Dimensions in millimetres

Specified thickness		Alloy number 1050, 1050A, 1070, 1070A, 1080, 1080A, 1085, 1100, 1200, 1100A, 1230A, 3003, 3103, 3203, 3005, 3105, 4006, 4007, 4015, 5005, 5010, 5110A, 5050, 8011A, 8021, 8079					
		Specified width					
Over	Up to and including	Up to and including 450	Over 450, up to and including 900	Over 900, up to and including 1 400	Over 1 400, up to and including 1 800	Over 1 800, up to and including 2 300	Over 2 300, up to and including 2 600
Tolerance							
≥ 0,15	0,20	±0,03	±0,03	±0,05			
0,20	0,25	±0,03	±0,04	±0,05			
0,25	0,45	±0,04	±0,04	±0,05	±0,06		
0,45	0,70	±0,04	±0,05	±0,06	±0,08		
0,70	0,90	±0,05	±0,05	±0,06	±0,09	±0,13	