
**Heat treatable steels, alloy steels and
free-cutting steels —**

**Part 5:
Nitriding steels**

*Aciers pour traitement thermique, aciers alliés et aciers pour
décolletage —*

Partie 5: Aciers pour nitruration

Sample Document

get full document from standards.iteh.ai



Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification and designation	3
4.1 Classification.....	3
4.2 Designation.....	3
5 Information to be supplied by the purchaser	3
5.1 Mandatory information.....	3
5.2 Options/supplementary or special requirements.....	3
5.3 Ordering example.....	4
6 Manufacturing process	4
6.1 General.....	4
6.2 Deoxidization.....	4
6.3 Heat treatment and surface condition at delivery.....	4
6.3.1 Normal condition at delivery.....	4
6.3.2 Particular heat-treatment condition.....	4
6.3.3 Particular surface conditions.....	4
6.4 Traceability of the cast.....	4
7 Requirements	4
7.1 Chemical composition, hardness and mechanical properties.....	4
7.1.1 General.....	4
7.1.2 Chemical composition.....	5
7.1.3 Mechanical properties.....	5
7.2 Machinability.....	5
7.3 Cold shearability.....	5
7.4 Grain size.....	5
7.5 Non-metallic inclusions.....	5
7.5.1 Microscopic inclusions.....	5
7.5.2 Macroscopic inclusions.....	5
7.6 Internal soundness.....	5
7.7 Surface quality.....	5
7.8 Decarburization.....	6
7.9 Shape, dimensions and tolerances.....	6
8 Inspection	6
8.1 Testing procedures and types of documents.....	6
8.2 Frequency of testing.....	7
8.3 Specific inspection and testing.....	7
8.3.1 Verification of the hardness and mechanical properties.....	7
8.3.2 Visual and dimensional inspection.....	7
9 Test methods	7
9.1 Chemical analysis.....	7
9.2 Hardness and mechanical tests.....	7
9.2.1 Hardness.....	7
9.2.2 Mechanical tests.....	7
9.2.3 Impact test.....	7
9.3 Retests.....	8
10 Marking	8
Annex A (normative) Ruling sections for mechanical properties	18
Annex B (normative) Supplementary or special requirements	22

Annex C (informative) Designation of steels given in this document and of comparable grades covered in various designation systems	24
Annex D (informative) Dimensional standards applicable to products complying with this document	25
Bibliography	26

Sample Document

get full document from standards.iteh.ai

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 4, *Heat treatable and alloy steels*.

This second edition cancels and replaces the first edition (ISO 683-5:2014), of which it constitutes a minor revision.

The main changes compared to the previous edition are as follows:

- in the Scope, “see [5.2](#)” has been added as a cross reference;
- in [3.1](#), note 1 to entry has been revised;
- in [5.2](#), the ordering example has been moved into a new subclause, as [5.3](#);
- in [7.7.3](#), the surface class given has been changed from A to 1z2;
- in [9.2.3](#), the option for retesting has been revised;
- Figure 3 has been renamed as [Table 9](#);
- in [A.2.1](#), the cross references have been corrected to [A.2.2](#) to [A.2.4](#).

A list of all parts in the ISO 683 series can be found on the ISO website.

Sample Document

get full document from standards.iteh.ai

Heat treatable steels, alloy steels and free-cutting steels —

Part 5: Nitriding steels

1 Scope

This document gives the technical delivery requirements for

- semi-finished products, e.g. blooms, billets, slabs (see note 1),
- bars (see note 1),
- wire rod,
- hot-rolled plates (see note 2), and
- hammer or drop forgings (see note 1)

manufactured from the nitriding steels listed in [Table 3](#) and supplied in one of the heat-treatment conditions given for the different types of products in [Table 1](#), rows 2 to 5, and in one of the surface conditions given in [Table 2](#).

The steels are generally intended for the fabrication of quenched and tempered and, subsequently, nitriding machine parts.

The requirements for mechanical properties given in this document are restricted to the sizes given in [Table 6](#).

NOTE 1 Hammer-forged semi-finished products (blooms, billets, slabs, etc.), seamless rolled rings and hammer-forged bars are in the following covered under semi-finished products or bars and not under the term “hammer and drop forgings”.

NOTE 2 The term “plate” includes in the following also wide flats unless otherwise stated.

In special cases, variations in these technical delivery requirements or additions to these requirements can form the subject of an agreement at the time of enquiry and order (see [5.2](#) and [Annex B](#)).

In addition to this document, the general technical delivery requirements of ISO 404 are applicable.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 148-1, *Metallic materials — Charpy pendulum impact test — Part 1: Test method*

ISO 377, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing*

ISO 404:2013, *Steel and steel products — General technical delivery requirements*

ISO 643, *Steels — Micrographic determination of the apparent grain size*

ISO 3887, *Steels — Determination of depth of decarburization*

ISO 4885, *Ferrous materials — Heat treatments — Vocabulary*

ISO 4948-1, *Steels — Classification — Part 1: Classification of steels into unalloyed and alloy steels based on chemical composition*

ISO 4948-2, *Steels — Classification — Part 2: Classification of unalloyed and alloy steels according to main quality classes and main property or application characteristics*

ISO/TS 4949, *Steel names based on letter symbols*

ISO 4967, *Steel — Determination of content of non-metallic inclusions — Micrographic method using standard diagrams*

ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 6929, *Steel products — Vocabulary*

ISO 7788, *Steel — Surface finish of hot-rolled plates and wide flats — Delivery requirements*

ISO 9443, *Heat-treatable and alloy steels — Surface quality classes for hot-rolled round bars and wire rods — Technical delivery conditions*

ISO/TR 9769, *Steel and iron — Review of available methods of analysis*

ISO 10474, *Steel and steel products — Inspection documents*

ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 377, ISO 4885, ISO 4948-1, ISO 4948-2, ISO 6929 and ISO 14284 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1 ruling section

section for which the specified mechanical properties shall apply

Note 1 to entry: Independent of the actual shape and dimensions of the cross-section of the product, the size of its ruling section is always given by a diameter. This corresponds to the diameter of an “equivalent round bar”. That is a round bar which will show the same cooling rate as the actual ruling section of the product concerned at its position for taking the test pieces when being cooled from austenitizing temperature.

3.2 nitriding steel

heat-treatable steel containing controlled amounts of the nitride forming elements, aluminium, chromium, molybdenum and/or vanadium and are particularly suited for nitriding

3.3 nitriding

heat treatment characterized by keeping a steel product for a sufficiently long time at temperatures below the transformation temperature AC1 in a nitrogen providing gaseous or liquid salt environment to achieve diffusion of the nitrogen into the steel surface

Note 1 to entry: An increase in surface hardness, wear resistance and fatigue properties is attained with this treatment.

4 Classification and designation

4.1 Classification

The classification of the relevant steel grades is allocated in accordance with ISO 4948-1 and ISO 4948-2. All steels covered by this document are classified as alloy special steels.

4.2 Designation

For the steel grades covered by this document, the steel names as given in the relevant tables are allocated in accordance with ISO/TS 4949.

The designation of steels given in this document and of comparable grades covered in various designation systems is given in [Annex C](#).

5 Information to be supplied by the purchaser

5.1 Mandatory information

The manufacturer shall obtain the following information from the purchaser at the time of enquiry and order:

- a) the quantity to be delivered;
- b) the designation of the product form (e.g. slab, bloom, billet, round bar, wire rod);
- c) either the designation of the dimensional standard and the dimensions and tolerances selected from this (see [7.9](#)) or the designation of the drawing or any other document covering the dimensions and tolerances required for the product;
- d) reference to this document, i.e. ISO 683-5;
- e) the designation of the steel grade given in [Table 3](#);
- f) designation for a test report 2.2 or, if required, any other type of inspection document in accordance with ISO 10474.

5.2 Options/supplementary or special requirements

A number of options are specified in this document and listed below in this subclause. If the purchaser does not indicate the wish to implement any of these options, the products will be supplied in accordance with the basic specification of this document (see [5.1](#)):

- a) if a heat-treatment condition other than the untreated condition is required, the symbol for this other condition (see [Table 1](#), column 2);
- b) if another surface condition than hot worked or a special surface quality is required, the surface condition (see [Table 2](#), column 2) and the surface quality (see [7.7](#));
- c) any supplementary requirement that shall be complied with, the symbol and, where necessary, the details of this supplementary requirement (see [Annex B](#));
- d) any requirement relating to the removal of surface defects (see [7.7.4](#));
- e) any requirement regarding the permissible depth of decarburization (see [7.8](#));
- f) impact test at a temperature lower than room temperature (see [9.2.3](#)).