
**Mechanical contraceptives —
Reusable natural and silicone
rubber contraceptive diaphragms —
Requirements and tests**

*Contraceptifs mécaniques — Diaphragmes contraceptifs réutilisables
en caoutchouc — Performances et essais*

Sample Document

get full document from standards.iteh.ai



Reference number
ISO 8009:2014(E)

© ISO 2014

Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Sampling	2
5 Classification	2
6 Materials	2
7 Design	2
7.1 General	2
7.2 Rim	2
7.3 Reinforcing spring	2
7.4 Spring ends	2
7.5 Dome and rim	3
8 Dimensions	3
8.1 Diameter	3
8.2 Dome thickness	3
9 Tensile properties of the dome	3
9.1 Tensile strength	3
9.2 Elongation at break	3
10 Mechanical properties of rim and spring — Type 1 and Type 2 diaphragms	4
10.1 Compression resistance	4
10.2 Twisting during compression	4
11 Freedom from visible defects	4
12 Test report	4
13 Packaging, labelling, and storage	5
13.1 Packaging	5
13.2 Labelling	5
13.3 Storage	5
Annex A (normative) Determination of size	7
Annex B (normative) Determination of dome thickness	8
Annex C (normative) Determination of tensile properties	9
Annex D (normative) Determination of deterioration after accelerated ageing by oven treatment	11
Annex E (normative) Determination of compression and fatigue resistances of coil-spring and flat-spring diaphragms	13
Annex F (normative) Determination of twisting during compression of coil-spring and flat spring diaphragms	16
Annex G (normative) Determination of visible defects	19
Annex H (normative) Test report	23
Annex I (normative) Instructions for care and use of reusable rubber contraceptive diaphragms	24
Bibliography	26

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 157, *Non-systemic contraceptives and STI barrier prophylactics*.

This second edition cancels and replaces the first edition, ISO 8009:2004, of which it constitutes a minor revision. It also incorporates the amendment ISO 8009:2004/Amd1:2012.

Introduction

Diaphragms are medical devices, therefore, they should be produced under a good quality management system. Reference should be made, for example to the ISO 9000- series, in conjunction with ISO 13485.

The sampling plans and acceptance quality limits (AQLs) given in this International Standard are for referee testing. The AQLs represent the maximum tolerable level of defects in the products. As diaphragms are intended for re-use, manufacturers should strive for entirely defect-free product.

Manufacturers can devise and apply additional and alternative quality control measures for their use and after production. These methods can differ among manufacturers.

Sample Document

get full document from standards.iteh.ai

Sample Document

get full document from standards.iteh.ai

Mechanical contraceptives — Reusable natural and silicone rubber contraceptive diaphragms — Requirements and tests

1 Scope

This International Standard specifies the minimum requirements and test methods to be used for reusable diaphragms made from natural rubber and silicone rubber. These diaphragms are intended for contraceptive use.

This International Standard is not applicable to other vaginal contraceptive barriers, such as those known as cervical caps, vaginal sponges, and vaginal sheaths.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 188, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 463, *Geometrical Product Specifications (GPS) — Dimensional measuring equipment — Design and metrological characteristics of mechanical dial gauges*

ISO 2859-1:1999, *Sampling procedures for inspection by attributes — Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection*

ISO 10993-1, *Biological evaluation of medical devices — Part 1: Evaluation and testing within a risk management process*

ISO 10993-5, *Biological evaluation of medical devices — Part 5: Tests for in vitro cytotoxicity*

ISO 10993-10, *Biological evaluation of medical devices — Part 10: Tests for irritation and skin sensitization*

3 Terms and definitions

For the purpose of this document, the terms and definitions given in ISO 2859-1 and the following apply.

3.1

lot

batch

collection of diaphragms of the same design, colour, shape, size, and formulation, manufactured at essentially the same time, using the same process, common lots of raw materials, common equipment and personnel

Note 1 to entry: The size of a lot is not specified in this International Standard, but it can be specified by a purchaser as part of a purchasing contract. Depending on the method of manufacture, multiple sizes can be produced in a defined lot/batch. In such cases, traceability can be maintained by using both the lot number and the size.

4 Sampling

Sampling and establishment of the sampling plan shall be carried out as described in ISO 2859-1.

NOTE It is necessary to know the lot size in order to derive from ISO 2859-1 the number of samples to be tested. The lot size varies among manufacturers, and is regarded as part of the process and quality controls used by the manufacturer.

5 Classification

Diaphragms shall be classified into the following types:

- a) **Type 1:** Coil-spring diaphragm, also known as a helically wound diaphragm.
- b) **Type 2:** Flat-spring diaphragm, also known as a flat-leaf diaphragm, watch-spring diaphragm, or *Mensinga* diaphragm.
- c) **Type 3:** Arcing-spring diaphragm, also known as an arcing-bend diaphragm or bow-bend diaphragm.

6 Materials

The diaphragm, excluding the spring, shall be made of a natural or silicone rubber compound.

For any new product or following a significant change to the formulation or manufacturing process, biocompatibility assessments shall be conducted in accordance with ISO 10993-1. Testing for cytotoxicity, in accordance with ISO 10993-5, and for irritation and sensitization, in accordance with ISO 10993-10, shall be conducted. Spermicides applied at the time of use are exempt from this requirement. Where practicable, manufacturers should take steps to recommend spermicides that minimize irritant effects. Accredited laboratories shall be used for all biocompatibility testing. Regulatory bodies might also specify local requirements and require results to be interpreted by a qualified toxicologist. Any toxicologist's assessment report shall state that the product is safe under normal conditions of use.

NOTE Many latex products that have been established as safe, including diaphragms and medical gloves, can exhibit a positive cytotoxic response when tested according to ISO 10993-5. While any cytotoxic effect can be of concern, it is primarily an indication of potential for *in vivo* toxicity, and a diaphragm cannot necessarily be determined to be unsuitable for use based solely on cytotoxicity data.

7 Design

7.1 General

The diaphragm shall consist of a dome and an integral peripheral rim. The dome of the diaphragm and the portion forming the rim shall be one continuous film.

7.2 Rim

The rim of the diaphragm shall be reinforced with a spring, which shall be sufficiently rigid to hold the rim in a flat, circular configuration.

7.3 Reinforcing spring

The reinforcing spring shall be completely encapsulated and centrally located within the rim.

7.4 Spring ends

The ends of the spring shall be joined in such a manner that the joint does not project through the surface of the rim.

7.5 Dome and rim

The dome and rim shall have a uniform, smooth, and non-tacky finish.

8 Dimensions

8.1 Diameter

The nominal diameters of preferred sizes shall be 55 mm, 60 mm, 65 mm, 70 mm, 75 mm, 80 mm, 85 mm, 90 mm, 95 mm, and 100 mm.

When tested in accordance with [Annex A](#), the two diameter measurements shall not differ by more than 4 % of the nominal size. The mean of these two measurements, called diaphragm diameter, shall equal the nominal size within a tolerance of ± 2 mm.

Examine 13 diaphragms of each size. No diaphragm diameter shall fall outside the limits.

8.2 Dome thickness

When tested in accordance with [Annex B](#), the thickness of the diaphragm dome at the thinnest point measured shall not be less than 0,20 mm.

9 Tensile properties of the dome

9.1 Tensile strength

When tested in accordance with [Annex C](#), the median tensile strength of 13 diaphragms of each size shall not be less than the values given in [Table 1](#).

When tested in accordance with [Annex D](#), the median tensile strength of 13 oven-treated diaphragms of each size shall not be less than the values given in [Table 1](#).

9.2 Elongation at break

When tested in accordance with [Annex C](#), the median elongation at break of 13 untreated diaphragms of each size shall not be less than the values given in [Table 1](#).

When tested in accordance with [Annex D](#), the median elongation at break of 13 oven-treated diaphragms of each size shall not be less than the values given in [Table 1](#).

Table 1 — Minimum median tensile properties

Property	Natural rubber untreated	Natural rubber oven-treated	Silicone rubber untreated	Silicone rubber oven-treated
Tensile strength, MPa	15	11	7	7
Elongation at break, %	650	500	350	350