
Safety of toys —
Part 3:
Migration of certain elements

Sécurité des jouets —

Partie 3: Migration de certains éléments

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 8124-3:2020

<https://standards.iteh.ai/catalog/standards/iso/99ac88c1-7054-45ef-aa4b-7ff9f8cab043/iso-8124-3-2020>



iTeh Standards
(<https://standards.itih.ai>)
Document Preview

ISO 8124-3:2020

<https://standards.itih.ai/catalog/standards/iso/99ac88c1-7054-45ef-aa4b-7ff9f8cab043/iso-8124-3-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	2
3 Terms and definitions	2
4 Maximum acceptable levels	3
4.1 Specific requirements	3
4.2 Interpretation of results	4
5 Principle	4
6 Reagents	4
7 Apparatus	5
8 Selection of test portions	5
9 Preparation and extraction of test portions	6
9.1 Coatings of paint, varnish, lacquer, printing ink, polymer and similar coatings	6
9.1.1 Test portion preparation	6
9.1.2 Extraction procedure	6
9.2 Polymeric and similar material, including laminates, whether textile-reinforced or not, but excluding other textiles	7
9.2.1 Test portion preparation	7
9.2.2 Extraction procedure	7
9.3 Paper and paperboard	7
9.3.1 Test portion preparation	7
9.3.2 Extraction procedure	7
9.4 Natural, artificial or synthetic textiles	8
9.4.1 Test portion preparation	8
9.4.2 Extraction procedure	8
9.5 Glass/ceramic/metallic materials	8
9.5.1 Test portion preparation	8
9.5.2 Extraction procedure	8
9.6 Other materials, whether mass-coloured or not (e.g. wood, fibreboard, bone and leather)	9
9.6.1 Test portion preparation	9
9.6.2 Extraction procedures	9
9.7 Materials intended to leave a trace	9
9.7.1 Test portion preparation for materials in solid form	9
9.7.2 Test portion preparation for materials in liquid form	10
9.7.3 Extraction procedure for samples not containing grease, oil, wax or similar material	10
9.7.4 Extraction procedure for samples containing grease, oil, wax or similar material	10
9.8 Pliable modelling materials, including modelling clays and gels	11
9.8.1 Test portion preparation	11
9.8.2 Extraction procedure for samples not containing grease, oil, wax or similar material	11
9.8.3 Extraction procedure for samples containing grease, oil, wax or similar material	12
9.9 Paints, including finger paints, varnishes, lacquers, glazing powders and similar material in solid or liquid form	12
9.9.1 Test portion preparation for materials in solid form	12
9.9.2 Test portion preparation for materials in liquid form	12
9.9.3 Extraction procedure for samples not containing grease, oil, wax or similar material	13

9.9.4	Extraction procedure for samples containing grease, oil, wax or similar material.....	13
10	Elemental analysis.....	13
10.1	Methods of analysis.....	13
10.2	Method detection limit (MDL).....	13
10.3	Calculation of results.....	14
11	Test report.....	14
Annex A	(normative) Sieve requirements.....	15
Annex B	(informative) Selection of procedure.....	16
Annex C	(informative) Methods for analysis of elements.....	17
Annex D	(informative) Background and rationale.....	23
Bibliography		29

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

ISO 8124-3:2020

<https://standards.itih.ai/catalog/standards/iso/99ac88c1-7054-45ef-aa4b-7ff9f8cab043/iso-8124-3-2020>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 181, *Safety of toys*.

This third edition cancels and replaces the second edition (ISO 8124-3:2010), which has been technically revised. It also incorporates the Amendments ISO 8124-3:2010/Amd.1:2014 and ISO 8124-3:2010/Amd.2:2018. The main changes to the previous edition are as follows:

- two detailed dewaxing methods have been introduced to replace the original one;
- an ICP-OES method for determination of the elements is given in [Annex C](#) as informative content.

A list of all parts in the ISO 8124 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.