

INTERNATIONAL  
STANDARD

**ISO**  
**8264**

First edition  
1989-11-15

---

---

**Hard coal — Determination of the swelling  
properties using a dilatometer**

*Houille — Détermination des propriétés de gonflement à l'aide d'un dilatomètre*

**Sample Document**

get full document from [standards.iteh.ai](https://standards.iteh.ai)



Reference number  
ISO 8264 : 1989 (E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 8264 was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*.

Sample Document

get full document from [standards.iteh.ai](https://standards.iteh.ai)

© ISO 1989

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

## Introduction

The Audibert-Arnu dilatometer test was adopted as ISO Recommendation ISO/R 349 : 1963 which was transformed into an International Standard ISO 349 : 1975. When reviewed in 1980, it was generally acknowledged that similar tests, using slightly different equipment and techniques, were used in various countries. One test in widespread use was that which measures the swelling properties of hard coal using the Ruhr dilatometer.

A thorough survey of the construction and operation of this instrument was made between 1973 and 1978 by a working group in the United Kingdom. Eleven laboratories participated in the work, including two which operated the Audibert-Arnu dilatometer as described in ISO 349. In the course of considerable inter-laboratory testing, the results indicated that values of contraction and dilatation found with the Audibert-Arnu dilatometer were higher and lower respectively than those found with the modified Ruhr dilatometer (the version described in this International Standard).

These differences were attributed to the fact that the excess material from the tapered test piece is removed from the wider end in the Audibert version of the dilatometer test and from the narrower end in the Ruhr version. The latter procedure ensures a test piece of greater and more uniform volume.

It is not intended that ISO 349 be withdrawn immediately, however it is suggested that the test be gradually phased out and replaced by that described in this International Standard, a test which has been tried and proven, particularly in the United Kingdom and the Federal Republic of Germany, and shown to be reliable and suitable for measuring the swelling properties of all types of hard coal.

# Sample Document

This page intentionally left blank

get full document from [standards.iteh.ai](https://standards.iteh.ai)

# Hard coal — Determination of the swelling properties using a dilatometer

## 1 Scope

This International Standard specifies a method for the measurement of the swelling of hard coal using a dilatometer.

## 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 428 : 1983, *Wrought copper-aluminium alloys — Chemical composition and forms of wrought products*.

ISO 683-1 : 1987, *Heat-treatable steels, alloy steels and free-cutting steels — Part 1: Direct-hardening unalloyed and low-alloyed wrought steel in form of different black products*.

ISO 1988 : 1975, *Hard coal — Sampling*.

## 3 Definitions

For the purposes of this International Standard, the following definitions apply.

**3.1 softening temperature; temperature of initial contraction:** The temperature at which the downward movement of the dilatometer piston is 0,5 mm.

NOTE — See  $\theta_1$  in figure 3.

**3.2 temperature of maximum contraction:** The temperature at which the dilatometer piston reaches its lowest point.

NOTE — See  $\theta_2$  in figure 3.

**3.3 resolidification temperature; temperature of maximum dilatation:** The temperature at which the dilatometer piston reaches its highest point.

NOTE — See  $\theta_3$  in figure 3.

**3.4 maximum contraction:** The maximum downward movement of the dilatometer piston, measured from the zero point and expressed as a percentage of the initial test piece length.

NOTE — See  $c$  in figures 3 and 4.

**3.5 maximum dilatation:** The maximum upward movement of the dilatometer piston after contraction, measured from the zero point and expressed as a percentage of the initial test piece length.

NOTE — See  $d$  in figures 3 and 4. The value can be either positive or negative.

**3.6 repeatability:** The maximum acceptable difference between two determinations which are carried out in the same laboratory, by the same operator with the same apparatus, on test pieces prepared from the same test sample and tested simultaneously in two different retorts during the same heating cycle or separately in the same retort during different heating cycles.

**3.7 reproducibility:** The maximum acceptable difference between the means of two determinations which are carried out in each of two laboratories, on representative portions taken from the same gross sample, after the last stage of sample preparation.

## 4 Principle

A test piece, in the form of a pencil, prepared from powdered coal is heated at a constant rate in a steel retort positioned in a furnace, the temperature monitoring system having been previously calibrated using two reference metals of known melting points. The change in level of a piston resting upon the test piece is observed continuously, and a record is produced which is characteristic of the swelling properties of the coal.

## 5 Materials

The following materials are required for temperature calibration (7.1).

**5.1 Graphite pencils,** 30 mm long, base diameter 7,4 mm, top diameter 6,8 mm, with a small cylindrical reservoir drilled in the narrow end of each pencil.