
**Tall-oil fatty acids for paints and
varnishes — Test methods and
characteristic values**

*Acides gras de tall-oil pour peintures et vernis — Méthodes d'essai et
valeurs caractéristiques*

Sample Document

get full document from standards.iteh.ai



Reference number
ISO 8623:2015(E)

© ISO 2015

Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Test methods and characteristic values	1
Annex A (normative) Determination of unsaponifiable matter (Diethyl ether method)	2
Annex B (normative) Determination of rosin acid content	5

Sample Document

get full document from standards.iteh.ai

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 35, *Paints and varnishes*, Subcommittee SC 10, *Test methods for binders for paints and varnishes*.

This second edition cancels and replaces the first edition (ISO 8623:1997), which has been technically revised with the following changes:

- the former requirements were changed to information on characteristic values;
- the data for unsaponifiable matter content was changed from mass fraction of max. 2,5 % to max. 5 %;
- the method for the determination of the unsaponifiable matter (diethyl ether method) was implemented from the 1980 edition of ISO 150 because it is no longer included in the actual revision of ISO 150, i.e. ISO 150:2006;
- the concentration of phenolphthalein indicator solution was changed from 10 g/l in ethanol to 5 g/l in ethanol or in a 1:1 ethanol/water mixture.

Introduction

Normally, requirements are agreed between the interested parties. So with this new edition, this International Standard no longer specifies requirements but only test methods and gives information on characteristic values for tall-oil fatty acids.

Sample Document

get full document from standards.iteh.ai