
**Evaluation of methods for assessing
the release of nanomaterials from
commercial, nanomaterial-containing
polymer composites**

*Évaluation des méthodes de détermination d'émission de
nanomatériaux par des polymères composites commerciaux,
contenant des nanomatériaux*

<https://standards.iteh.ai>
Document Preview

[ISO/TR 22293:2021](https://standards.iteh.ai/catalog/standards/iso/28dff551-0fc4-4023-9c6a-beb2d0f0f821/iso-tr-22293-2021)

<https://standards.iteh.ai/catalog/standards/iso/28dff551-0fc4-4023-9c6a-beb2d0f0f821/iso-tr-22293-2021>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO/TR 22293:2021](https://standards.iteh.ai/catalog/standards/iso/28dff551-0fc4-4023-9c6a-beb2d0f0f821/iso-tr-22293-2021)

<https://standards.iteh.ai/catalog/standards/iso/28dff551-0fc4-4023-9c6a-beb2d0f0f821/iso-tr-22293-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	v
Introduction.....	vi
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Abbreviations.....	3
5 Understanding the nano-enabled products.....	4
5.1 Pathway analysis for the supply chain.....	4
5.2 Matrix and MNM characteristics affecting rate and form of release.....	8
5.2.1 General.....	8
5.2.2 Consideration of the polymer used in the composite.....	9
5.2.3 Polymer degradation.....	10
5.2.4 Consideration of MNM used in the composite.....	10
5.2.5 Polymer nanocomposites.....	11
5.2.6 Application areas and use phase (or lifecycle) processes.....	12
6 Factors affecting release measurement method selection.....	15
6.1 General.....	15
6.2 Forms of release.....	16
6.3 Decision support framework to determine which transformations need consideration with examples.....	21
7 Approaches to detecting and quantifying the released material associated with added manufactured nanomaterials.....	23
7.1 General.....	23
7.2 Methods for sampling released material.....	23
7.2.1 General.....	23
7.2.2 Sampling material released into air.....	24
7.2.3 Sampling material released into water, solids, and biological fluids.....	25
7.3 Methods for preparing samples of released material for subsequent analysis.....	26
7.3.1 General.....	26
7.3.2 Preparation and analysis of air samples.....	26
7.3.3 Preparation and analysis of waters, solids and biological fluid samples.....	27
7.4 Measurement challenges.....	28
7.4.1 General.....	28
7.4.2 Surface functionalization and transformations.....	28
7.4.3 Sample collection artefacts.....	29
7.4.4 Applicability of a measurement method for a given release media.....	29
7.4.5 Sample preparation artefacts.....	29
7.4.6 Capability of a measurement method.....	29
7.4.7 Representativeness of measurements.....	30
7.4.8 Composition measurements.....	30
7.4.9 Polymer stability.....	30
7.4.10 Commercial practices.....	30
7.5 Considerations for detection, quantification, and determination of properties of released materials.....	31
7.6 Applicable measurement methods.....	32
8 Identification of needs for standards, methods, instrumentation, decision frameworks, and research.....	32
8.1 General.....	32
8.2 Potential improved/new methods.....	32
8.3 Inter-laboratory studies.....	33
8.4 Protocols and assays.....	34

8.5	Opportunities for standardization of methods.....	34
8.6	Decision frameworks.....	35
Annex A (informative) Example case studies.....		38
Bibliography.....		57

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO/TR 22293:2021](https://standards.iteh.ai/catalog/standards/iso/28dff551-0fc4-4023-9c6a-beb2d0f0f821/iso-tr-22293-2021)

<https://standards.iteh.ai/catalog/standards/iso/28dff551-0fc4-4023-9c6a-beb2d0f0f821/iso-tr-22293-2021>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 229, *Nanotechnologies*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

<https://standards.iteh.ai/>

<https://standards.iteh.ai/catalog/standards/iso/28dff551-0fc4-4023-9c6a-beb2d0f0f821/iso-tr-22293-2021>

Introduction

0.1 General

The use of manufactured nanomaterials (MNM) in consumer products and applications is growing as manufacturers exploit the unique properties of nanomaterials. MNMs are an increasingly common feature of a growing variety of commercial applications and consumer products — from computer chips to golf clubs. So too are concerns over what is or can be released from products containing MNMs, and the risk and potential impacts of exposure to such releases. These unique properties offer significant commercial value, enabling the manufacture of products that offer novel characteristics. The MNM might be embedded in solids, might be suspended in fluid, or might be bound to the surface of solid products. An understanding of what is released from products containing MNMs is critical to planning and managing safe development and use of those products.

This document aims to contribute to that understanding by providing a guide to the information to be taken into account in determining the methods for identifying and evaluating releases of MNMs from matrices; providing a framework for understanding how these methods and the information they produce can support decision-making; and identifying opportunities for developing standards in this area.

This document provides practical support for decisions related to product development and use through early consideration of the potential for release of MNM and through focus on realistic use scenarios where exposures to the released MNM might occur.

The intended users of this document would include:

- those planning to develop or adapt technical specifications for MNM use in commercial products;
- risk managers, product developers, exposure measurement practitioners or other stakeholders seeking guidance on the availability and utility of methods to measure releases that could occur from uses of specific MNMs in composites;
- methods and instrumentation developers seeking to identify needs of the risk management community;
- those planning basic and applied research programs for measurement and modelling to support decisions around sustainably safe uses of MNMs.

The structured review of the information regarding the selection of MNM measurement methods provided in this document is needed because technologies to produce MNMs, their uses, and MNM measurement methods are often developing at the same time, and the development of measurement methods can in some cases lag behind product development needs. Furthermore, the need to measure particular characteristics of the released MNM might also evolve as greater understanding of what might cause toxicity for a particular kind of MNM is gained. This relationship between emerging measurement methods and emerging information about toxicity makes a structured approach to review of measurement needs even more important, so that data are assembled to support decisions using the most up-to-date and fit-to-purpose measurement methods. Finally, the selection process for choosing a particular MNM-composite for a product should include the consideration of whether the available measurement methods are feasible for the evaluating the conditions of use of that MNM-composite. This consideration is needed because many methods available for research or for controlled conditions in industrial hygiene settings are not useful for realistic measurement needs where consumers might be exposed. In some cases, those methods are too difficult to conduct outside of the laboratory, and in other cases the methods are too labour-intensive to be feasible for routine decision support.

The development of the decision-making framework presented in this document is based in large part on initial analyses that focused on releases from polyamide or epoxy polymers to which multi-wall carbon nanotubes (MWCNT) have been added. Nonetheless, the framework can be used to inform the selection of methods for identifying and evaluating the releases for a wide range of MNMs and types of matrices, as illustrated by the case studies in [Annex A](#). The case studies have been chosen because of the availability of information and methods relevant for actual MNM-polymer composite uses.

Release from polymer nanocomposites can occur through processes such as physical, chemical, or thermal degradation of a polymer matrix, resulting in particles that might include a mixture of free MNM, free polymer, and matrix-bound MNM. This document focuses on the first release to human exposure or to an effluent pathway. While acknowledging that subsequent MNM fate and transport could follow from this initial release, the primary concern of this document is whether and where release of MNMs can occur in the context of consumer or commercial use, and the need to monitor likelihood of human exposure potential. Although other stages of the lifecycle of products containing MNMs are discussed briefly to provide context, subsequent fate and transport events are not addressed in detail.

The ultimate goal is to use the report structure of this document as a foundation for addressing releases of other MNMs from other matrices in subsequent versions of the document.

0.2 Decision-Making Framework

0.2.1 General

In developing the decision-making framework set out in this document two key concepts that have proven useful in addressing the relevant risk management issues in support of decision-making have been applied. The first is “problem formulation”^[1]. This describes the purpose and context of the analysis, and the nature of the decision that the analysis aims to support. By making it clear the analysis is being conducted to support a specific decision, this approach helps to ensure the analysis remains focused on methods that have practical application in making that decision. The second key concept is “fit for purpose.” In other words, the nature of the analytical approach used should be sufficient for and appropriate to addressing the specific risk management decision. This includes assuring that the depth of analysis - including consideration of the sources and potential magnitude of uncertainty - is consistent with the information needed to support the decision. In the context of this document, this means that feasibility is an important consideration in the choice of analytical methods.

0.2.2 Application of concepts

In applying these concepts to the selection of methods for identifying and evaluating releases of MNMs from matrices, the problem formulation would include an evaluation of the potential for human exposure to the component of the nano-enabled product (NEP) that contains the MNM and the potential for MNM release from that component.

To evaluate the potential for human exposure, an understanding of the product design and the potential use scenarios is required. If, for example, the component containing the MNM is fully encased within a consumer product, or is part of a machine where it is accessible only during maintenance, there are limited opportunities for human exposure as part of the release event. Description of potential use scenarios is also critical for understanding the potential nature of human exposure (e.g. direct dermal contact vs. inhalation of released MNM), as well as relevant conditions of potential wear and aging (e.g. potential and nature of abrasion, temperature, presence or absence of water and UV light).

Together, these elements of the problem formulation can aid in determining which potential release scenarios need to be tested, as well as the nature of the analytical methods needed and, thus, aid in determining whether it is feasible to evaluate the risk of a given choice of product composition without substantial investment in analytical methods development.

0.2.3 Tiered approach

In some situations, a tiered approach — such as those described in [Clause 8](#) — can be useful. For example, if release outside of a confined structure is not expected (e.g. if the MNM is contained within a phone, and release would not result in consumer exposure), an analytical method that simply detects the MNM could be sufficient. In other cases, a qualitative description might be useful to predict the potential for further interactions with other materials, and ultimately the fate and transport of the MNM. Such information could be used, for example, in deciding between alternative designs or products

0.2.4 Quantitative risk assessment presents challenges