
Papir, karton in lepenka, namenjeni za stik z živili - Ugotavljanje obstojnosti barve v obarvanem papirju, kartonu in lepenki

Paper and board intended to come into contact with foodstuffs - Determination of colour fastness of dyed paper and board

Papier und Pappe vorgesehen für den Kontakt mit Lebensmitteln - Bestimmung der Farbechtheit von gefärbtem Papier und Pappe

Papiers et cartons destinés à entrer en contact avec les denrées alimentaires - Détermination de la solidité de la couleur des papiers et cartons colorés

Ta slovenski standard je istoveten z: prEN 646

ICS:

67.250	Materiali in predmeti v stiku z živili	Materials and articles in contact with foodstuffs
85.060	Papir, karton in lepenka	Paper and board

oSIST prEN 646:2026**en,fr,de**

Sample Document

get full document from standards.iteh.ai

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 646

May 2026

ICS 67.250; 85.060

Will supersede EN 646:2018

English Version

Paper and board intended to come into contact with foodstuffs - Determination of colour fastness of dyed paper and board

Papiers et cartons destinés à entrer en contact avec les
denrées alimentaires - Détermination de la solidité de
la couleur des papiers et cartons colorés

Papier und Pappe vorgesehen für den Kontakt mit
Lebensmitteln - Bestimmung der Farbechtheit von
gefärbtem Papier und Pappe

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 172.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Principle	4
5 Materials and equipment	5
5.1 General	5
5.2 Unstained glass fibre papers of 60 mm × 90 mm	5
5.3 Glass plates, 60 mm × 90 mm.	5
5.4 Polyethylene film, uncoloured and transparent.	5
5.5 Weight, having a mass of 1 kg	5
5.6 Grey scale	5
5.7 Drying cupboard	5
5.8 Kettle	5
5.9 Cotton gloves	5
5.10 Adjacent glass rods	5
6 Reagents	5
6.1 Distilled or deionised water	5
6.2 Aqueous acetic acid, 3,0 % (m/V).	5
6.3 Alkaline salt solution, see Table 1, composition of the alkaline salt with a pH value of 8,6 ± 0,1.	5
6.4 Castor oil or sunflower oil, with specification of vegetable oil that should be as defined in Regulation (EU) No 10/2011 [1].	6
7 Sampling	6
8 Preparation of test pieces	6
9 Procedure	6
10 Test conditions	7
11 Evaluation	7
12 Test Report	8
Annex A (normative) Determination of colour fastness of dyed paper and board on large samples	9
Annex B (informative) Precision data	10
Bibliography	13

prEN 646:2026(E)**European foreword**

This document (prEN 646:2026) has been prepared by Technical Committee CEN/TC 172 “Pulp, paper and board”, the secretariat of which is held by DIN.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 646:2018.

This document includes the following significant technical changes with respect to EN 646:2018:

- a) Update of materials and equipment (Clause 5);
- b) modification of the type of oil which can be used (6.4);
- c) precision in evaluating the staining (Clause 11);
- d) addition of an Annex on precision data (Annex B);
- e) revision of Annex A;
- f) editorial changes.

Sample Document

get full document from standards.iteh.ai