

SLOVENSKI STANDARD

SIST EN 13445-11:2026

01-september-2026

Nadomešča:

SIST EN 13445-11:2024

Nekurjene tlačne posode - 11. del: Dodatne zahteve za tlačne posode iz titana in titanovih zlitin

Unfired pressure vessels - Part 11: Additional requirements for pressure vessels of titanium and titanium alloys

Unbefeuerte Druckbehälter - Teil 11: Zusätzliche Anforderungen an Druckbehälter aus Titan und Titanlegierungen

Récipients sous pression non soumis à la flamme - Partie 11 : Exigences supplémentaires pour les récipients sous pression en titane et alliage de titane

Ta slovenski standard je istoveten z: EN 13445-11:2026

ICS:

23.020.32	Tlačne posode	Pressure vessels
77.150.50	Titanovi izdelki	Titanium products

SIST EN 13445-11:2026

en,fr,de

Sample Document

get full document from standards.iteh.ai

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 13445-11

July 2026

ICS 23.020.30

Supersedes EN 13445-11:2024

English Version

**Unfired pressure vessels - Part 11: Additional
requirements for pressure vessels of titanium and
titanium alloys**

Réipients sous pression non soumis à la flamme -
Partie 11 : Exigences supplémentaires pour les
réipients sous pression en titane et alliage de titane

Unbefeuerte Druckbehälter - Teil 11: Zusätzliche
Anforderungen an Druckbehälter aus Titan und
Titanlegierungen

This European Standard was approved by CEN on 24 June 2026.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2026 CEN All rights of exploitation in any form and by any means reserved
worldwide for CEN national Members.

Ref. No. EN 13445-11:2026 E

Contents

Page

European foreword.....	4
1 Scope	5
2 Normative references	5
3 Terms, definitions, symbols and units	6
4 General requirements	6
5 Materials.....	6
5.1 General	6
5.2 Material specification	6
5.3 Material grouping system	6
5.4 Material documentation	6
5.5 Prevention of brittle fracture	7
6 Design	7
6.1 General	7
6.2 Corrosion, erosion and protection	7
6.3 Joint coefficient	7
6.4 Time-independent nominal design stress	7
6.5 Creep design	8
6.6 Shells under external pressure	9
6.7 Flanges	9
6.8 Fatigue design	9
7 Manufacture	10
7.1 General	10
7.2 Filler metals	10
7.3 Attachment of dissimilar metals	10
7.4 Backing strips, joggle joints and partial penetration welds	10
7.5 Qualification of welding procedure specifications (WPQR)	10
7.6 Qualification of welders and welding operators	10
7.7 Joint preparation	10
7.8 Execution of welded joints	11
7.9 Preheat	11
7.10 Permanent joints other than welding	11
7.11 Production test, reference criteria	12
7.12 Extent of testing	12
7.13 Performance of test and acceptance criteria	12
7.14 Forming procedures	12
7.14.1 Cold forming	12
7.14.2 Hot forming	13
7.15 Heat treatment after forming	13
7.15.1 General	13
7.15.2 Heat treatment of flat products after cold forming	13
7.15.3 Heat treatment of tubular products after cold forming	14
7.15.4 Heat treatment after hot forming	14
7.15.5 Annealing	14
7.16 Sampling of formed products	15

7.16.1 Cold formed products without heat treatment.....	15
7.16.2 Hot formed or cold formed products with heat treatment.....	15
7.17 Tests	16
7.17.1 Base material	16
7.17.2 Butt welds.....	16
7.18 Post weld heat treatment (PWHT)	16
7.19 Repairs.....	16
8 Inspection and testing.....	16
8.1 General	16
8.2 Non-destructive testing of welded joints	16
8.2.1 General	16
8.2.2 Demonstration of satisfactory experience for testing group 3	17
8.3 Determination of extent of non-destructive testing	18
8.4 Selection of non destructive testing methods for internal imperfections	21
8.5 Selection of non destructive testing methods for surface imperfections.....	21
8.6 Assessment of defects	21
8.7 Standard hydrostatic test	22
9 Finishing operations.....	22
Annex A (normative) Grouping system for titanium and titanium alloys.....	23
Annex B (informative) Designation of some titanium and titanium alloy materials.....	24
Annex C (informative) Materials.....	25
C.1 General	25
C.2 ISO material specifications.....	25
C.3 ASME and ASTM material specifications.....	26
C.4 DIN material specifications.....	27
Annex D (informative) Physical properties of titanium and titanium alloys.....	28
D.1 Definitions.....	28
D.1.1 Density.....	28
D.1.2 Poisson's ratio.....	28
D.2 Physical properties of titanium and titanium alloys	28
D.2.1 General	28
D.2.2 Polynomial coefficients	28
D.2.3 Figures for physical properties of titanium and titanium alloys	29
Annex E (informative) Creep data for unalloyed titanium	31
Annex Y (informative) History of EN 13445-11	32
Y.1 Differences between EN 13445-11:2024 and EN 13445-11:2026	32
Annex ZA (informative) Relationship between this European Standard and the Essential Requirements of Directive 2014/68/EU aimed to be covered.....	33
Bibliography	35

EN 13445-11:2026 (E)**European foreword**

This document (EN 13445-11:2026) has been prepared by Technical Committee CEN/TC 54 “Unfired pressure vessels”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2026, and conflicting national standards shall be withdrawn at the latest by December 2026.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13445-11:2024.

Annex Y provides details of corrections and changes between this European Standard and the previous edition.

This document has been prepared under a standardization request addressed to CEN by the European Commission. The Standing Committee of the EFTA States subsequently approves these requests for its Member States.

For the relationship with EU Legislation, see informative Annex ZA, which is an integral part of this document.

A list of all parts in the EN 13445 series can be found on the CEN website.

Although these Parts may be obtained separately, it should be recognized that the Parts are interdependent. As such, the manufacture of unfired pressure vessels requires the application of all the relevant Parts in order for the requirements of the Standard to be satisfactorily fulfilled.

Corrections to the standard interpretations where several options seem possible are conducted through the Migration Help Desk (MHD). Information related to the Help Desk can be found at <https://unm.fr/en/maintenance-agencies/maintenance-agency-en-13445/>. A form for submitting questions can be downloaded from the link to the MHD website. After subject experts have agreed an answer, the answer will be communicated to the questioner. Corrected pages will be given specific issue number and issued by CEN according to CEN Rules. Interpretation sheets will be posted on the website of the MHD.

Any feedback and questions on this document should be directed to the users’ national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

1 Scope

This document specifies requirements for unfired pressure vessels and their parts made of titanium and titanium alloys in addition to the general requirements for unfired pressure vessels under EN 13445-1:2026 to EN 13445-5:2026.

NOTE 1 Cast materials, HIP and additive manufacturing are not included in this version. Details regarding such materials will be subject to an amendment to or a revision of this European Standard.

NOTE 2 Materials in Groups 51.4 and 54 are not included in this version.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 764-5:2014, *Pressure equipment - Part 5: Inspection documentation of metallic materials and compliance with the material specification*

EN 10204:2004, *Metallic products — Types of inspection documents*

EN 13445-1:2026, *Unfired pressure vessels — Part 1: General*

EN 13445-2:2026, *Unfired pressure vessels — Part 2: Materials*

EN 13445-3:2026, *Unfired pressure vessels — Part 3: Design*

EN 13445-4:2026, *Unfired pressure vessels — Part 4: Fabrication*

EN 13445-5:2026, *Unfired pressure vessels — Part 5: Inspection and testing*

EN ISO 148-1:2016, *Metallic materials — Charpy pendulum impact test — Part 1: Test method (ISO 148-1:2016)*

EN ISO 9606-5:2000, *Approval testing of welders — Fusion welding — Part 5: Titanium and titanium alloys, zirconium and zirconium alloys (ISO 9606-5:2000)*

EN ISO 15614-5:2024, *Specification and qualification of welding procedures for metallic materials — Welding procedure test — Part 5: Arc welding of titanium, zirconium and their alloys (ISO 15614-5:2024)*

EN ISO 15614-8:2016, *Specification and qualification of welding procedures for metallic materials — Welding procedure test — Part 8: Welding of tubes to tube-plate joints (ISO 15614-8:2016)*

EN ISO 15608:2025, *Welding — Grouping system for metallic materials (ISO 15608:2025)*

3 Terms, definitions, symbols and units

For the purposes of this document, the terms, definitions, symbols and units given in EN 13445-1:2026 to EN 13445-5:2026 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 General requirements

The general requirements of EN 13445-1:2026 shall apply.

5 Materials

5.1 General

The general requirements of EN 13445-2:2026 shall apply with the following additions/exclusions in 5.2 to 5.5.

There are presently no European Standards or European Approval of Materials (EAMs) specifically for titanium and titanium alloys for pressure purposes. This document is therefore limited to the use of Particular Materials Appraisal (PMA).

5.2 Material specification

The material specification shall specify the composition limits for all constituents, heat treatment and the appropriate mechanical properties for acceptance and other purposes.

Only material having a minimum elongation after fracture of not less than 10 %, in its final fabricated state, shall be used for construction of pressure vessels. The specified minimum elongation after fracture shall be measured on a gauge length as defined in EN 13445-2:2026, 4.1.4.

NOTE To achieve this it can be necessary to start with a higher elongation after fracture, e.g. 14 %, prior to cold forming.

5.3 Material grouping system

EN 13445-2:2026, Annex A, is not applicable to pressure vessels of titanium and titanium alloys and is replaced by Annex A of this document.

The grouping system for titanium and titanium alloys shown in Table A.1 of this document is based on EN ISO 15608:2025. However, only the grades included in Annex B of this document are considered suitable for welded pressure vessel construction.

5.4 Material documentation

Materials for pressure bearing parts compliant with the requirements of this document shall be accompanied by inspection documentation in accordance with EN 10204:2004.

The type of inspection document shall be in accordance with EN 764-5:2014 and include an affirmation of compliance to the material specification.

5.5 Prevention of brittle fracture

There are no general requirements for titanium and titanium alloys at temperatures down to

- -100 °C for group 51.1 and 51.2, and
- -60 °C for all other Groups.

Below these temperatures adequate toughness shall be demonstrated by impact testing of a Charpy-V-notch test specimen (according to EN ISO 148-1:2016) at a temperature not higher than the minimum metal temperature T_M achieving a mean impact energy KV of 27 J in the base material, welds, and heat affected zones. The impact tests shall be carried out in accordance with the requirements of EN 13445-2:2026, B.3.

NOTE For practical reasons, a test temperature of -196 °C is commonly used for all impact testing of titanium and titanium alloys for any minimum metal temperature below -100 °C .

Alternatively, a fracture mechanics approach in line with EN 13445-2:2026, Annex B method 3 may be employed.

6 Design

6.1 General

All the requirements included in EN 13445-3:2026 shall apply, with the following amendments, given in 6.2 to 6.7.

Physical properties of titanium and titanium alloys are given in Annex D of this document.

6.2 Corrosion, erosion and protection

Unalloyed titanium and titanium alloys have outstanding resistance to a wide range of reducing, neutral and oxidizing corrosive media. As a general rule no allowance is required for pitting or general corrosion.

Caution is required in the design of joints and the selection of gasket materials where crevice corrosion could occur.

6.3 Joint coefficient

For normal operating load cases the value of joint coefficient z is given in Table 6.3-1. It is related to the testing group of the governing welded joints.

Testing groups are specified in 8.2 of this document.

Table 6.3-1 — Joint coefficient and corresponding testing group

z	1	0,8
Testing group	1	3

Testing groups 2 and 4 are not permitted for pressure vessels made of titanium and titanium alloys.

6.4 Time-independent nominal design stress

The design stress for titanium and titanium alloy materials entering service in the annealed condition following removal of test coupons at the material manufacturer's works, shall be derived in accordance with Table 6.4-1.