
Embalaža - Načrtovanje za recikliranje plastične embalaže - 11. del: Postopek za ocenjevanje zmožnosti recikliranja plastične embalaže - Protokoli za togo embalažo iz polietilen tereftalata (razen PET-plasten)

Packaging - Design for recycling of plastic packaging - Part 11: Recyclability evaluation process for plastic packaging - Protocols for PET rigid packaging (except bottles)

Verpackung - Recyclingorientierte Gestaltung von Kunststoffverpackungsprodukten - Teil 11: Verfahren zur Bewertung der Recyclingfähigkeit von Kunststoffverpackungen - Protokolle für starre Verpackungen aus PET (außer Flaschen)

Emballages - Conception des emballages plastiques en vue de leur recyclage - Partie 11 : Processus d'évaluation de la recyclabilité des emballages plastiques - Protocoles pour les emballages rigides en PET (hors bouteilles)

Ta slovenski standard je istoveten z: EN 18120-11:2026

ICS:

13.030.50	Recikliranje	Recycling
55.020	Pakiranje in distribucija blaga na splošno	Packaging and distribution of goods in general
83.080.20	Plastomeri	Thermoplastic materials

SIST EN 18120-11:2026

en,fr,de

Sample Document

get full document from standards.iteh.ai

EUROPEAN STANDARD

EN 18120-11

NORME EUROPÉENNE

EUROPÄISCHE NORM

April 2026

ICS 13.030.50; 55.020

English Version

Packaging - Design for recycling of plastic packaging - Part 11: Recyclability evaluation process for plastic packaging - Protocols for PET rigid packaging (except bottles)

Emballages - Conception des emballages plastiques en vue de leur recyclage - Partie 11: Processus d'évaluation de la recyclabilité des emballages plastiques - Protocoles pour les emballages rigides en PET (hors bouteilles)

Verpackung - Recyclingorientierte Gestaltung von Kunststoffverpackungsprodukten - Teil 11: Verfahren zur Bewertung der Recyclingfähigkeit von Kunststoffverpackungen - Protokolle für starre Verpackungen aus PET (außer Flaschen)

This European Standard was approved by CEN on 9 February 2026.

This European Standard was corrected and reissued by the CEN-CENELEC Management Centre on 22 April 2026.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2026 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN 18120-11:2026 E

Contents	Page
European foreword	3
Introduction	4
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Recyclability evaluation process	7
4.1 Principle	7
4.1.1 General	7
4.1.2 Targeted uses and retained recycling technology	8
4.1.3 List of applicable unit operations for PET rigid packaging (except bottles) and corresponding test procedures	8
4.2 Testing procedures for pretreatment - Flake preparation	10
4.2.1 Grinding	10
4.2.2 Pretreatment description for prewashing, hot washing, delamination, and rinsing	11
4.2.3 Prewashing	11
4.2.4 Hot washing	11
4.2.5 Delamination (for multilayer material)	12
4.2.6 Hot rinsing	12
4.2.7 Cold rinsing and floatation	12
4.2.8 Drying	13
4.2.9 Air elutriation	14
4.2.10 Assessment report, standard testing procedure and recommended benchmark values ..	14
4.3 Testing procedures for treatment - Pellet extrusion	16
4.3.1 Flakes blending for subsequent extrusion	16
4.3.2 Extrusion - Pellet production	16
4.3.3 Crystallization	17
4.3.4 Solid state polymerization	17
4.3.5 Assessment report, standard testing procedures and recommended benchmark values ..	18
4.4 Testing procedures for conversion into test samples	20
4.4.1 Pellet blends preparation	20
4.4.2 Conversion route 1 - Plaque injection moulding	20
4.4.3 Conversion route 2 - Sheet extrusion	20
4.4.4 Assessment report, standard testing procedure and recommended benchmark values ..	20
Annex A (informative) Virgin material examples and its characteristics	22
Bibliography	23

European foreword

This document (EN 18120-11:2026) has been prepared by Technical Committee CEN/TC 261 “Packaging”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2026, and conflicting national standards shall be withdrawn at the latest by October 2026.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a standardization request addressed to CEN by the European Commission. The Standing Committee of the EFTA States subsequently approves these requests for its Member States.

Any feedback and questions on this document should be directed to the users’ national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Sample Document

get full document from standards.iteh.ai

EN 18120-11:2026 (E)**Introduction**

The EN 18120 series, under the general title *Packaging — Design for recycling of plastic packaging*, which aims via a series of guidelines and protocols to establish consistency and improvement for the design for recycling of household, industrial and commercial plastic packaging, consists of the following parts:

- *Part 1: Definitions and principles for design-for-recycling of plastic packaging*
- *Part 3: Evaluation processes for the sortability of plastic packaging*
- *Part 4: Guideline for PET bottles*
- *Part 5: Guideline for PET rigid packaging (except bottles)*
- *Part 6: Guideline for PE and PP rigid packaging*
- *Part 7: Guideline for PE and PP flexible packaging*
- *Part 8: Guideline for PS and XPS rigid packaging*
- *Part 9: Guideline for EPS packaging*
- *Part 10: Recyclability evaluation process for plastic packaging — Protocols for PET bottles*
- *Part 11: Recyclability evaluation process for plastic packaging — Protocols for PET rigid packaging (except bottles)*
- *Part 12: Recyclability evaluation process for plastic packaging — Protocols for PE and PP rigid packaging*
- *Part 13: Recyclability evaluation process for plastic packaging — Protocols for PE and PP flexible packaging*
- *Part 14: Recyclability evaluation process for plastic packaging — Protocols for PS and XPS rigid packaging*
- *Part 15: Recyclability evaluation process for plastic packaging — Protocols for EPS packaging*

Design for recycling guidelines are a common way of evaluating the compatibility with plastic-packaging collection, sorting and recycling which enables the use of secondary raw materials that are of sufficient quality when compared to the original material, in state-of-the-art facilities.

They provide guidance on the level of compatibility, defined as:

- green: packaging constituents and components with full compatibility with state-of-the-art collection, sorting and recycling;
- yellow: packaging constituents and components with limited compatibility with state-of-the-art collection, sorting and recycling;
- red: packaging constituents and components which are not compatible with state-of-the-art collection, sorting and recycling.

The design for recycling guidelines provided in the EN 18120 series cover the design for recycling based on the knowledge available at the time of the development of this document and are representative of the

state-of-the-art. They consider packaging waste collection, sorting and recycling, so that the recycled plastic can substitute primary raw materials in packaging application or other applications. Compliance with the design guidelines in the EN 18120 series does not guarantee that the recycled plastic quality will be fit for purpose for a specific targeted end application or compliant with applicable regulations.

Packaging recyclability is the combination of design of recycling, proven collection, sorting and recycling in practice.

Sample Document

get full document from standards.iteh.ai