
Aluminij in aluminijeve zlitine - Kemična sestava in oblika gnetenih izdelkov - 3.
del: Kemična sestava in oblika izdelkov

Aluminium and aluminium alloys - Chemical composition and form of wrought products -
Part 3: Chemical composition and form of products

Aluminium und Aluminiumlegierungen - Chemische Zusammensetzung und Form von
Halbzeug - Teil 3: Chemische Zusammensetzung und Erzeugnisformen

Aluminium et alliages d'aluminium - Composition chimique et forme des produits
corroyés - Partie 3 : Composition chimique et forme des produits

Ta slovenski standard je istoveten z: EN 573-3:2026

ICS:

77.040.30	Kemijska analiza kovin	Chemical analysis of metals
77.150.10	Aluminijski izdelki	Aluminium products

SIST EN 573-3:2026**en,fr,de**

Sample Document

get full document from standards.iteh.ai

EUROPEAN STANDARD

EN 573-3

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2026

ICS 77.150.10

Supersedes EN 573-3:2019+A2:2023

English Version

Aluminium and aluminium alloys - Chemical composition and form of wrought products - Part 3: Chemical composition and form of products

Aluminium et alliages d'aluminium - Composition
chimique et forme des produits corroyés - Partie 3 :
Composition chimique et forme des produits

Aluminium und Aluminiumlegierungen - Chemische
Zusammensetzung und Form von Halbzeug - Teil 3:
Chemische Zusammensetzung und Erzeugnisformen

This European Standard was approved by CEN on 2 February 2026.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2026 CEN All rights of exploitation in any form and by any means reserved
worldwide for CEN national Members.

Ref. No. EN 573-3:2026 E

Contents	Page
European foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Chemical composition limits	4
5 Writing rules	5
6 Alloy designations	5
7 Sequence of elements	5
8 Rounding rules for determination of compliance	6
Annex A (informative) Form of products	32
A.1 General	32
A.2 European Standards	32
Annex B (normative) Guidelines for the introduction of new wrought aluminium and wrought aluminium alloys in CEN/TC 132 standards	51
B.1 General principles	51
B.2 Rules for introduction of new alloys	51
B.3 Procedure for introduction of new alloys	51
Bibliography	52

European foreword

This document (EN 573-3:2026) has been prepared by Technical Committee CEN/TC 132 “Aluminium and aluminium alloys”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2026, and conflicting national standards shall be withdrawn at the latest by September 2026.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 573-3:2019+A2:2023.

EN 573-3:2026 includes the following significant technical changes with respect to EN 573-3:2019+A2:2023:

- addition of the alloy EN AW-2007C in Tables 2 and A.2;
- addition of the alloy EN AW-2079 in Tables 2 and A.2;
- addition of the alloy EN AW-4115A in Tables 4 and A.4;
- addition of the alloy EN AW-6084 in Tables 6 and A.6;
- modification of the order of alloys to conform with Aluminium Association System.

EN 573 comprises the following parts under the general title *Aluminium and aluminium alloys — Chemical composition and form of wrought products*:

- *Part 1: Numerical designation system;*
- *Part 2: Chemical symbol based designation system;*
- *Part 3: Chemical composition and form of products;*
- *Part 4: Forms of products;*
- *Part 5: Codification of standardized wrought products.*

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

EN 573-3:2026 (E)

1 Scope

This document specifies the chemical composition limits of wrought aluminium and wrought aluminium alloys and form of products.

NOTE The chemical composition limits of aluminium and aluminium alloys specified herein are completely identical with those registered with the Aluminium Association, 1525, Wilson Boulevard, Suite 600, Arlington, VA 22209, USA, for the corresponding alloys.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 573-1, *Aluminium and aluminium alloys — Chemical composition and form of wrought products — Part 1: Numerical designation system*

EN 573-2, *Aluminium and aluminium alloys — Chemical composition and form of wrought products — Part 2: Chemical symbol based designation system*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Chemical composition limits

The chemical composition of aluminium and aluminium alloys is specified in percentage by mass in Table 1 to Table 8. Limits of impurities are expressed as a maximum; limits of alloying elements shown as a range. Aluminium is specified as a minimum for unalloyed aluminium, and as a remainder for aluminium alloys.

The chemical composition of internationally registered wrought aluminium and wrought aluminium alloys not listed in this document can be found in Teal sheets [2] or their Addendum [3].

Analysis shall be made for elements which are specified, for example Pb, Sn, Bi, Sb, Zr.

5 Writing rules

5.1 Standard limits for alloying elements and impurities are expressed in percentage by mass to the following decimal places:

— less than 0,001 %	0,000X;
— 0,001 % but less than 0,01 %	0,00X;
— 0,01 % but less than 0,10 %:	
— unalloyed aluminium made by a refining process	0,0XX;
— others	0,0X;
— 0,10 % to 0,55 %	0,XX;
— over 0,55 %	0,X; X,X; XX,X.

Exception: combined Si + Fe limits for 1xxx designations shall be expressed as 0,XX or 1,XX.

5.2 The aluminium content for unalloyed aluminium made by a refining process is the difference between 100,00 % and the sum of all other metallic elements present in amounts of 0,001 0 % or more each, expressed to the third decimal place before determining the sum, which is rounded to the second decimal place before subtracting.

For unalloyed aluminium not made by a refining process, the aluminium content is the difference between 100,00 % and the sum of all other metallic elements present in amounts of 0,010 % or more each expressed to the second decimal place before determining the sum.

6 Alloy designations

To introduce new wrought aluminium and wrought aluminium alloys in standards, Annex B shall be followed.

The numerical designation systems used in Teal sheets and European Standards for wrought aluminium alloys are identical. As specified in EN 573-1 the prefix "EN AW-" shall be added to the 4-digits designation of the alloy.

The alternative chemical symbol based alloy designation system shall be based on EN 573-2.

Both the numerical and the chemical symbol based designations are indicated in Table 1 to Table 8. The list of applicable form(s) of products for a specific alloy is provided at Annex A.

The International numerical system is the preferred one. The chemical symbol based designations are indicated for reference only.

7 Sequence of elements

Standard limits for alloying elements and impurities are expressed in the following sequence: silicon, iron, copper, manganese, magnesium, chromium, nickel, zinc, titanium, gallium, vanadium, remarks, other elements - each, other elements - total, aluminium.

Limits of additional specified elements are inserted in alphabetical order of their chemical symbols under "Remarks".

8 Rounding rules for determination of compliance

In recording chemical analysis test results, the number representing the result for any element specified in this document shall be expressed to the same number of decimal places as the corresponding number in this document. For unalloyed aluminium, the aluminium content is derived as described in 5.2.

The following rounding rules shall be used for determination of compliance with this document:

- a) when the figure immediately after the last figure to be retained is less than 5, the last figure to be retained remains unchanged;
- b) when the figure immediately after the last figure to be retained is greater than 5, or equal to 5 and followed by at least one figure other than 0, the last figure to be retained is increased by 1;
- c) when the figure immediately after the last figure to be retained is equal to 5 and followed by zeros only, the last figure to be retained remains unchanged if even and is increased by 1 if odd.

Sample Document

get full document from standards.iteh.ai

Table 1 — Aluminium — 1000 series

Alloy designation		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Remarks	Others ^a		Aluminium min.
Numerical	Chemical symbols													Each	Total b	
EN AW-1050A	EN AW-Al 99,5	0,25	0,40	0,05	0,05	0,05	-	-	0,07	0,05	-	-	-	0,03	-	99,50 ^c
EN AW-1060	EN AW-Al 99,6	0,25	0,35	0,05	0,03	0,03	-	-	0,05	0,03	-	0,05	-	0,03	-	99,60 ^c
EN AW-1070A	EN AW-Al 99,7	0,20	0,25	0,03	0,03	0,03	-	-	0,07	0,03	-	-	-	0,03	-	99,70 ^c
EN AW-1080A	EN AW-Al 99,8(A)	0,15	0,15	0,03	0,02	0,02	-	-	0,06	0,02	0,03	-	e	0,02	-	99,80 ^c
EN AW-1085	EN AW-Al 99,85	0,10	0,12	0,03	0,02	0,02	-	-	0,03	0,02	0,03	0,05	-	0,01	-	99,85 ^c
EN AW-1090	EN AW-Al 99,90	0,07	0,07	0,02	0,01	0,01	-	-	0,03	0,01	0,03	0,05	-	0,01	-	99,90 ^c
EN AW-1098	EN AW-Al 99,98	0,010	0,006	0,003	-	-	-	-	0,015	0,003	-	-	-	0,003	-	99,98 ^d
EN AW-1100	EN AW-Al 99,0Cu	0,95 Si + Fe		0,05–0,20	0,05	-	-	-	0,10	-	-	-	e	0,05	0,15	99,00 ^c
EN AW-1200	EN AW-Al 99,0	1,00 Si + Fe		0,05	0,05	-	-	-	0,10	0,05	-	-	e	0,05	0,15	99,00 ^c
EN AW-1200A	EN AW-Al 99,0(A)	1,00 Si + Fe		0,10	0,30	0,30	0,10	-	0,10	-	-	-	-	0,05	0,15	99,00 ^c
EN AW-1110	EN AW-Al 99,1	0,30	0,8	0,04	0,01	0,25	0,01	-	-	-	-	-	0,02B; 0,03V + Ti	0,03	0,15	99,10 ^c
EN AW-1235	EN AW-Al 99,35	0,65 Si + Fe		0,05	0,05	0,05	-	-	0,10	0,06	-	0,05	-	0,03	-	99,35 ^c
EN AW-1350	EN AW-Al 99,5	0,10	0,40	0,05	0,01	-	0,01	-	0,05	-	0,03	-	0,05 B; 0,02 V + Ti	0,03	0,10	99,50 ^c

EN 573-3:2026 (E)

Alloy designation		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Remarks	Others ^a		Aluminium min.
Numerical	Chemical symbols													Each	Total ^b	
EN AW-1350A	EN AW-Al 99,5(A)	0,25	0,40	0,02	-	0,05	-	-	0,05	-	-	-	0,03 Cr + Mn + Ti + V	0,03	-	99,50 ^c
EN AW-1450	EN AW-Al 99,5Ti	0,25	0,40	0,05	0,05	0,05	-	-	0,07	0,10-0,20	-	-	e	0,03	-	99,50 ^c
EN AW-1370	EN AW-Al 99,7	0,10	0,25	0,02	0,01	0,02	0,01	-	0,04	-	0,03	-	0,02 B; 0,02 V + Ti	0,02	0,10	99,70 ^c
EN AW-1198	EN AW-Al 99,98(A)	0,010	0,006	0,006	0,006	-	-	-	0,010	0,006	0,006	-	-	0,003	-	99,98 ^d
EN AW-1199	EN AW-Al 99,99	0,006	0,006	0,006	0,002	0,006	-	-	0,006	0,002	0,005	0,005	-	0,002	-	99,99 ^d

^a "Others" includes listed elements for which no specific limit is shown as well as unlisted metallic elements. The producer may analyse samples for trace elements not specified in the registration or specification. However, such analysis is not required and might not cover all metallic "Other" elements. Should any analysis by the producer or the purchaser establish that an "Others" element exceeds the limit of "Each" or that the aggregate of several "Others" elements exceeds the limit of "Total", the material shall be considered non-conforming.

^b The sum of those "Others" metallic elements 0,010 % or more each, expressed to the second decimal place before determining the sum.

^c The aluminium content for unalloyed aluminium not made by a refining process is the difference between 100,00 % and the sum of all other metallic elements present in amounts of 0,010 % or more each, expressed to the second decimal place before determining the sum.

^d The aluminium content for unalloyed aluminium made by a refining process is the difference between 100,00 % and the sum of all other metallic elements present in amounts of 0,001 0 % or more each, expressed to the third decimal before determining the sum, which is rounded to the second decimal place before subtracting.

^e 0,000 3 max. Be for welding electrode, welding rod and filler wire only.

Table 2 — Aluminium alloys — 2000 series — Al Cu

Alloy designation		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Remarks	Others ^a		Aluminium min.
Numerical	Chemical symbols													Each	Total ^b	
EN AW-2001	EN AW-Al Cu5,5MgMn	0,20	0,20	5,2- 6,0	0,15 - 0,50	0,20 - 0,45	0,10	0,05	0,10	0,20	-	-	0,05 Zr ^c	0,05	0,15	Remainder
EN AW-2007	EN AW-Al Cu4PbMgMn	0,8	0,8	3,3- 4,6	0,50 - 1,0	0,40 - 1,8	0,10	0,20	0,8	0,20	-	-	d	0,10	0,30	Remainder
EN AW-2007C	EN AW-Al Cu4MgMnBi(C)	0,8	0,8	3,3 - 4,6	0,20 - 1,0	0,40 - 1,8	0,10	0,20	0,8	0,20	-	-	0,10 - 1,0 Bi 0,10 Pb	0,05	0,15	Remainder
EN AW-2011	EN AW-Al Cu6BiPb	0,40	0,7	5,0 - 6,0	-	-	-	-	0,30	-	-	-	e	0,05	0,15	Remainder
EN AW-2011A	EN AW-Al Cu6BiPb(A)	0,40	0,50	4,5 - 6,0	-	-	-	-	0,30	-	-	-	e	0,05	0,15	Remainder
EN AW-2014	EN AW-Al Cu4SiMg	0,50 - 1,2	0,7	3,9 - 5,0	0,40 - 1,2	0,20 - 0,8	0,10	-	0,25	0,15	-	-	f	0,05	0,15	Remainder
EN AW-2014A	EN AW-Al Cu4SiMg(A)	0,50 - 0,9	0,50	3,9 - 5,0	0,40 - 1,2	0,20 - 0,8	0,10	0,10	0,25	0,15	-	-	0,20 Zr+Ti	0,05	0,15	Remainder
EN AW-2214	EN AW-Al Cu4SiMg(B)	0,50 - 1,2	0,30	3,9 - 5,0	0,40 - 1,2	0,20 - 0,8	0,10	-	0,25	0,15	-	-	f	0,05	0,15	Remainder
EN AW-2016	EN AW-Al Cu4SiMgAg	0,30 - 0,7	0,15	3,5 - 4,5	0,10 - 0,50	0,30 - 0,8	-	-	-	0,05 - 0,15	-	-	Ag 0,30 - 0,7 Zr 0,10 - 0,25	0,05	0,15	Remainder
EN AW-2017A	EN AW-Al Cu4MgSi(A)	0,20 - 0,8	0,7	3,5 - 4,5	0,40 - 1,0	0,40 - 1,0	0,10	-	0,25	-	-	-	0,25 Zr+Ti	0,05	0,15	Remainder
EN AW-2117	EN AW-Al Cu2,5Mg	0,8	0,7	2,2 - 3,0	0,20	0,20 - 0,50	0,10	-	0,25	-	-	-	-	0,05	0,15	Remainder
EN AW-2618A	EN AW-Al Cu2Mg1,5Ni	0,15 - 0,25	0,9 - 1,4	1,8 - 2,7	0,25	1,2 - 1,8	-	0,8 - 1,4	0,15	0,20	-	-	0,25 Zr+Ti	0,05	0,15	Remainder

EN 573-3:2026 (E)

Alloy designation		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Remarks	Others ^a		Aluminium min.
Numerical	Chemical symbols													Each	Total ^b	
EN AW-2219	EN AW-Al Cu6Mn	0,20	0,30	5,8 – 6,8	0,20 – 0,40	0,02	-	-	0,10	0,02 – 0,10	-	0,05 – 0,15	0,10 – 0,25 Zr	0,05	0,15	Remainder
EN AW-2319	EN AW-Al Cu6Mn(A)	0,20	0,30	5,8 – 6,8	0,20 – 0,40	0,02	-	-	0,10	0,10 – 0,20	-	0,05 – 0,15	0,10 – 0,25 Zr h	0,05	0,15	Remainder
EN AW-2024	EN AW-Al Cu4Mg1	0,50	0,50	3,8 – 4,9	0,30 – 0,9	1,2 – 1,8	0,10	-	0,25	0,15	-	-	f	0,05	0,15	Remainder
EN AW-2124	EN AW-Al Cu4Mg1(A)	0,20	0,30	3,8 – 4,9	0,30 – 0,9	1,2 – 1,8	0,10	-	0,25	0,15	-	-	f	0,05	0,15	Remainder
EN AW-2030	EN AW-Al Cu4PbMg	0,8	0,7	3,3 – 4,5	0,20 – 1,0	0,50 – 1,3	0,10	-	0,50	0,20	-	-	0,20 Bi ; 0,8 – 1,5 Pb	0,10	0,30	Remainder
EN AW-2031	EN AW-Al Cu2,5NiMg	0,50 – 1,3	0,6 – 1,2	1,8 – 2,8	0,50	0,6 – 1,2	-	0,6 – 1,4	0,20	0,20	-	-	-	0,05	0,15	Remainder
EN AW-2033	EN AW-Al Cu2,5MnSiMgBi	0,10 – 1,2	0,7	2,2 – 2,7	0,40 – 1,0	0,20 – 0,6	0,15	0,15	0,50	0,10	-	-	Bi: 0,05 – 0,8	0,05	0,15	Remainder
EN AW-2077	EN AW-Al Cu4,5MgMnSiBi	0,40 – 1,0	0,7	4,0 – 5,0	0,6 – 1,2	0,6 – 1,2	0,20	0,20	0,25	0,15	-	-	Li: 0,15 Bi: 0,20 – 0,9 Ag: 0,15 Zr: 0,15	0,05	0,15	Remainder
EN AW-2079	EN AW-Al Cu3,5Zn1Li1	0,12	0,15	3,0 – 3,8	0,10 – 0,35	0,05 – 0,35	-	-	0,8 – 1,2	0,10	-	-	0,8 – 1,0 Li 0,05 – 0,15 Zr	0,05	0,15	Remainder

Alloy designation		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Remarks	Others ^a		Aluminium min.
Numerical	Chemical symbols													Each	Total ^b	
EN AW-2091	EN AW-Al Cu2Li2Mg1,5	0,20	0,30	1,8 – 2,5	0,10	1,1 – 1,9	0,10	-	0,25	0,10	-	-	0,04 – 0,16 Zr g	0,05	0,15	Remainder

^a “Others” includes listed elements for which no specific limit is shown as well as unlisted metallic elements. The producer may analyse samples for trace elements not specified in the registration or specification. However, such analysis is not required and might not cover all metallic “Other” elements. Should any analysis by the producer or the purchaser establish that an “Others” element exceeds the limit of “Each” or that the aggregate of several “Others” elements exceeds the limit of “Total”, the material shall be considered non-conforming.

^b The sum of those “Others” metallic elements 0,010 % or more each, expressed to the second decimal place before determining the sum.

^c 0,003 max. Pb.

^d 0,20 Bi; 0,8–1,5 Pb; 0,20 Sn.

^e 0,20–0,6 Bi; 0,20–0,6 Pb.

^f Zr + Ti limit of 0,20 maximum may be used for extruded and forged products if mutually agreed by supplier or manufacturer and purchaser.

^g 1,7–2,3 Li.

^h 0,000 3 max. Be for welding electrode, welding rod and filler wire only.

Sample Document

get full document from standards.iteh.ai

EN 573-3:2026 (E)

Table 3 — Aluminium alloys — 3000 series — Al Mn

Alloy designation		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Remarks	Others ^a		Aluminium min.
Numerical	Chemical Symbols													Each	Total ^b	
EN AW-3002	EN AW-Al Mn _{0,2} Mg _{0,1}	0,08	0,10	0,15	0,05 – 0,25	0,05 – 0,20	-	-	0,05	0,03	-	0,05	-	0,03	0,10	Remainder
EN AW-3102	EN AW-Al Mn _{0,2}	0,40	0,7	0,10	0,05 – 0,40	-	-	-	0,30	0,10	-	-	-	0,05	0,15	Remainder
EN AW-3003	EN AW-Al Mn ₁ Cu	0,6	0,7	0,05 – 0,20	1,0 – 1,5	-	-	-	0,10	-	-	-	-	0,05	0,15	Remainder
EN AW-3103	EN AW-Al Mn ₁	0,50	0,7	0,10	0,9 – 1,5	0,30	0,10	-	0,20	-	-	-	0,10 Zr+Ti ^c	0,05	0,15	Remainder
EN AW-3103A	EN AW-Al Mn ₁ (A)	0,50	0,7	0,10	0,7 – 1,4	0,30	0,10	-	0,20	0,10	-	-	0,10 Zr+Ti	0,05	0,15	Remainder
EN AW-3004	EN AW-Al Mn ₁ Mg ₁	0,30	0,7	0,25	1,0 – 1,5	0,8 – 1,3	-	-	0,25	-	-	-	-	0,05	0,15	Remainder
EN AW-3104	EN AW-Al Mn ₁ Mg ₁ Cu	0,6	0,8	0,05 – 0,25	0,8 – 1,4	0,8 – 1,3	-	-	0,25	0,10	0,05	0,05	-	0,05	0,15	Remainder
EN AW-3005	EN AW-Al Mn ₁ Mg _{0,5}	0,6	0,7	0,30	1,0 – 1,5	0,20 – 0,6	0,10	-	0,25	0,10	-	-	-	0,05	0,15	Remainder
EN AW-3005A	EN AW-Al Mn ₁ Mg _{0,5} (A)	0,7	0,8	0,30	1,0 – 1,5	0,20 – 0,6	0,10	-	0,40	0,10	-	-	-	0,05	0,15	Remainder
EN AW-3105	EN AW-Al Mn _{0,5} Mg _{0,5}	0,6	0,7	0,30	0,30 – 0,8	0,20 – 0,8	0,20	-	0,40	0,10	-	-	-	0,05	0,15	Remainder
EN AW-3105A	EN AW-Al Mn _{0,5} Mg _{0,5} (A)	0,6	0,7	0,30	0,30 – 0,8	0,20 – 0,8	0,20	-	0,25	0,10	-	-	-	0,05	0,15	Remainder
EN AW-3105B	EN AW-Al Mn _{0,6} Mg _{0,5}	0,7	0,9	0,30	0,30 – 0,9	0,20 – 0,8	0,20	-	0,50	0,10	-	-	0,10 Pb	0,05	0,15	Remainder
EN AW-3017	EN AW-Al Mn ₁ Cu _{0,3}	0,25	0,25 – 0,45	0,25 – 0,40	0,8 – 1,2	0,10	0,15	-	0,10	0,05	-	-	-	0,05	0,15	Remainder
EN AW-3207	EN AW-Al Mn _{0,6}	0,30	0,45	0,10	0,40 – 0,8	0,10	-	-	0,10	-	-	-	-	0,05	0,10	Remainder

Alloy designation		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ga	V	Remarks	Others ^a		Aluminium min.
Numerical	Chemical Symbols													Each	Total ^b	
EN AW-3207A	EN AW-Al Mn0,6(A)	0,35	0,6	0,25	0,30 – 0,8	0,40	0,20	-	0,25	-	-	-	-	0,05	0,15	Remainder

^a “Others” includes listed elements for which no specific limit is shown as well as unlisted metallic elements. The producer may analyse samples for trace elements not specified in the registration or specification. However, such analysis is not required and might not cover all metallic “Other” elements. Should any analysis by the producer or the purchaser establish that an “Others” element exceeds the limit of “Each” or that the aggregate of several “Others” elements exceeds the limit of “Total”, the material shall be considered non-conforming.

^b The sum of those “Others” metallic elements 0,010 % or more each, expressed to the second decimal place before determining the sum.

^c 0,000 3 max. Be for welding electrode, welding rod and filler wire only.

Sample Document

get full document from standards.iteh.ai