



SLOVENSKI STANDARD SIST EN ISO 14577-1:2026

01-oktober-2026

Nadomešča:

SIST EN ISO 14577-1:2015

Kovinski materiali - Instrumentirano vtiskanje pri preskušanju trdote in drugih lastnosti materialov - 1. del: Preskusna metoda (ISO 14577-1:2026)

Metallic materials - Instrumented indentation test for hardness and materials parameters
- Part 1: Test method (ISO 14577-1:2026)

Metallische Werkstoffe - Instrumentierte Eindringprüfung zur Bestimmung der Härte und
anderer Werkstoffparameter - Teil 1: Prüfverfahren (ISO 14577-1:2026)

Matériaux métalliques - Essai de pénétration instrumenté pour la détermination de la
dureté et de paramètres des matériaux - Partie 1: Méthode d'essai (ISO 14577-1:2026)

Ta slovenski standard je istoveten z: EN ISO 14577-1:2026

ICS:

77.040.10 Mehansko preskušanje kovin Mechanical testing of metals

SIST EN ISO 14577-1:2026

en,de

Sample Document

get full document from standards.iteh.ai

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 14577-1

June 2026

ICS 77.040.10

Supersedes EN ISO 14577-1:2015

English Version

**Metallic materials - Instrumented indentation test for
hardness and materials parameters - Part 1: Test method
(ISO 14577-1:2026)**

Matériaux métalliques - Essai de pénétration
instrumenté pour la détermination de la dureté et de
paramètres des matériaux - Partie 1: Méthode d'essai
(ISO 14577-1:2026)

Metallische Werkstoffe - Instrumentierte
Eindringprüfung zur Bestimmung der Härte und
anderer Werkstoffparameter - Teil 1: Prüfverfahren
(ISO 14577-1:2026)

This European Standard was approved by CEN on 13 May 2026.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2026 CEN All rights of exploitation in any form and by any means reserved
worldwide for CEN national Members.

Ref. No. EN ISO 14577-1:2026 E

Contents	Page
European foreword.....	3

Sample Document

get full document from standards.iteh.ai

European foreword

This document (EN ISO 14577-1:2026) has been prepared by Technical Committee ISO/TC 164 "Mechanical testing of metals" in collaboration with Technical Committee CEN/TC 459/SC 1 "Test methods for steel (other than chemical analysis)" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2026, and conflicting national standards shall be withdrawn at the latest by December 2026.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 14577-1:2015.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 14577-1:2026 has been approved by CEN as EN ISO 14577-1:2026 without any modification.

Sample Document

get full document from standards.iteh.ai



International Standard

ISO 14577-1

Metallic materials — Instrumented indentation test for hardness and materials parameters —

Part 1: Test method

*Matériaux métalliques — Essai de pénétration instrumenté pour
la détermination de la dureté et de paramètres des matériaux —*

Partie 1: Méthode d'essai

**Third edition
2026-06**

ISO 14577-1:2026(en)

Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2026

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

© ISO 2026 – All rights reserved

ISO 14577-1:2026(en)

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Symbols and designations	2
5 Principle	4
6 Testing machine	5
7 Test piece	5
8 Procedure	6
9 Uncertainty of the results	9
10 Test report	10
Annex A (normative) Materials parameters determined from the force/indentation depth data set	12
Annex B (informative) Types of control use for the indentation process	25
Annex C (normative) Machine compliance and indenter area function	26
Annex D (informative) Notes on diamond indenters	28
Annex E (normative) Influence of the test piece surface roughness on the accuracy of the results	29
Annex F (informative) Correlation of indentation hardness H_{IT} to Vickers hardness	30
Annex G (normative) Determination of drift and minimizing creep influence	32
Annex H (informative) Estimation of uncertainty of the calculated values of hardness and materials parameters	34
Annex I (normative) Calculation of radial displacement correction	39
Bibliography	43

ISO 14577-1:2026(en)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 3, *Hardness testing*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 459/SC1, *Test methods for steel (other than chemical analysis)*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 14577-1:2015), which has been technically revised.

The main changes are as follows:

- Better specification of the approach speed of the tip.
- Addition of a loading method with constant strain rate.
- Change of order of hardness definitions: first H_{IT} then HM.
- Better proposals for cleaning the tip.
- Differentiation between contact area under load and in unloaded state.
- Complete reformulation of normative [Annex I](#) for radial displacement correction.

A list of all parts in the ISO 14577 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

ISO 14577-1:2026(en)**Introduction**

Hardness has typically been defined as the resistance of a material to permanent penetration by another harder material. The results obtained when performing Rockwell, Vickers, and Brinell tests are determined after the test force has been removed. Therefore, the effect of elastic deformation under the indenter has been ignored.

ISO 14577 (all parts) has been prepared to enable the user to evaluate the indentation of materials by considering both the force and displacement during plastic and elastic deformation. By monitoring the complete cycle of increasing and removal of the test force, hardness values equivalent to traditional hardness values can be determined. More significantly, additional properties of the material, such as its indentation modulus and elasto-plastic hardness, can also be determined. All these values can be calculated without the need to measure the indent optically. Furthermore, by a variety of techniques, the instrumented indentation test allows to record hardness and modulus depth profiles within a, probably complex, indentation cycle.

Although the indentation modulus (E_{IT}) value obtained in this test method is not directly equivalent to Young's modulus or the orientation specific elastic modulus of the material indented, E_{IT} is, however, equivalent to the isotropic Hill average of the elastic plane strain modulus of the material when there is no pile up and no residual stress.

ISO 14577 (all parts) has been written to allow a wide variety of post-test data analysis.

Part 1 of ISO 14577 specifies the method of indentation test for determination of instrumented indentation hardness and material properties.

Sample Document

get full document from standards.iteh.ai

Sample Document

get full document from standards.iteh.ai

Metallic materials — Instrumented indentation test for hardness and materials parameters —

Part 1: Test method

1 Scope

This document specifies the method of instrumented indentation test for determination of hardness and other materials parameters for the following three ranges:

- macro range: $2\text{ N} \leq F \leq 30\text{ kN}$;
- micro range: $2\text{ N} > F$; $h > 0,2\text{ }\mu\text{m}$;
- nano range: $h \leq 0,2\text{ }\mu\text{m}$.

For the nano range, the mechanical deformation strongly depends on the real shape of indenter tip and the calculated material parameters are significantly influenced by the contact area function of the indenter used in the testing machine. Therefore, careful calibration of both instrument and indenter shape is required in order to achieve an acceptable reproducibility of the materials parameters determined with different machines.

The macro and micro ranges are distinguished by the test forces in relation to the indentation depth.

Attention is drawn to the fact that the micro range has an upper limit given by the test force (2 N) and a lower limit given by the indentation depth of 0,2 μm .

The determination of hardness and other material parameters is given in the normative [Annex A](#).

At high contact pressures, damage to the indenter is possible. For test pieces with very high hardness and modulus of elasticity, permanent indenter deformation can occur and can be detected using suitable reference materials. Indentations that result in damage or permanent deformation of the indenter are excluded from the scope of this test method.

This test method can also be applied to thin metallic and non-metallic coatings and non-metallic materials. In this case, it is recommended that the specifications in the relevant standards be taken into account (see also [7.3](#) and ISO 14577-4).

The analysis methods of this standard assume that materials behave like ideal materials. Any deviation (internal stress, pile-up, sink-in, densification, phase transitions, cracks) will result in additional uncertainties. This becomes especially important if comparisons shall be done to material parameters, obtained with other methods.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 14577-2:2026, *Metallic materials — Instrumented indentation test for hardness and materials parameters — Part 2: Verification and calibration of testing machines*

ISO 14577-1:2026(en)

ISO/IEC Guide 98-3:2008, *Uncertainty of measurement — Part 3: Guide to the expression of uncertainty in measurement (GUM:1995)*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Symbols and designations

For the purposes of this document, the symbols and designations in [Table 1](#) shall be applied (see also [Figure 1](#) and [Figure 2](#)).

Table 1 — Symbols and designations

Symbol	Designation	Unit
$A_p(h_c)$	Projected area of contact under load of the indenter at distance h_c from the tip	mm ²
$A_{p,UL}(h_c)$	Projected area of contact in unloaded state of the indenter at distance h_c from the tip	mm ²
$A_s(h)$	Surface area of the indenter at distance h from the tip in unloaded state	mm ²
C_{IT}	Indentation creep	%
C_T	Total measured compliance of the contact (dh/dF tangent to the force removal curve at maximum test force)	nm/mN
C_F	Machine compliance	nm/mN
C_S	Compliance of the contact after correction for machine compliance	nm/mN
E_{IT}	Indentation modulus of the test piece	GPa
E_r	Reduced plane strain modulus of the contact (combination of test piece and indenter plane strain moduli)	GPa
F	Test force	N
F_{max}	Maximum test force	N
h	Indentation depth under applied test force	mm
h_c	Contact depth of the indenter with the test piece at F_{max}	mm
h_{max}	Maximum indentation depth at F_{max}	mm
h_p	Permanent indentation depth after removal of the test force	mm
h_r	Point of intersection of the tangent c to curve b at F_{max} with the indentation depth-axis as identified on Figure 1	mm
H_{IT}	Indentation hardness	GPa
HM	Martens hardness	GPa
HM_s	Martens hardness, determined from the slope of the increasing force/indentation depth curve	GPa
HM_{diff}	Martens hardness, determined from the first derivative of h vs $\sqrt{F}$	GPa
ν_s	Poisson's ratio of the test piece	
r	Radius of spherical indenter	mm
R_{IT}	Indentation relaxation	%

NOTE 1 To avoid very long numbers, the use of multiples or sub-multiples of the units can be used.

NOTE 2 The continued use of the unit N/mm² is allowed. 1 MPa = 1 N/mm².


ISO 14577-1:2026(en)

Table 1 (continued)

Symbol	Designation	Unit
W_{elast}	Elastic reverse deformation work of indentation	N·m
W_{total}	Total mechanical work of indentation	N·m
α	Cone semi-angle or angle of facet to the indentation axis for pyramidal indenters	°
θ	Maximum angle between the contact surface and the indenter for calculation of radial displacement	°
η_{IT}	Ratio $W_{\text{elast}}/W_{\text{total}}$	%

NOTE 1 To avoid very long numbers, the use of multiples or sub-multiples of the units can be used.

NOTE 2 The continued use of the unit N/mm² is allowed. 1 MPa = 1 N/mm².



- a Application of the test force.
- b Removal of the test force.
- c Tangent to curve b at F_{max} .

Figure 1 — Schematic representation of the test procedure