
**Kovinski materiali - Natezni preskus pri velikih hitrostih deformacije - 1. del:
Sistemi z elastičnim drogom (ISO 26203-1:2025)**

Metallic materials - Tensile testing at high strain rates - Part 1: Elastic-bar-type systems
(ISO 26203-1:2025)

Metallische Werkstoffe - Zugversuch bei hohen Dehngeschwindigkeiten - Teil 1:
Elastische Stoßwellentechnik (ISO 26203-1:2025)

Matériaux métalliques - Essai de traction à vitesses de déformation élevées - Partie 1:
Systèmes de type à barre élastique (ISO 26203-1:2025)

Ta slovenski standard je istoveten z: **EN ISO 26203-1:2025**

ICS:

77.040.10 Mehansko preskušanje kovin Mechanical testing of metals

SIST EN ISO 26203-1:2026**en,de**

Sample Document

get full document from standards.iteh.ai

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 26203-1

December 2025

ICS 77.040.10

Supersedes EN ISO 26203-1:2018

English Version

Metallic materials - Tensile testing at high strain rates - Part 1: Elastic-bar-type systems (ISO 26203-1:2025)

Matériaux métalliques - Essai de traction à vitesses de
déformation élevées - Partie 1: Systèmes de type à
barre élastique (ISO 26203-1:2025)

Metallische Werkstoffe - Zugversuch bei hohen
Dehngeschwindigkeiten - Teil 1: Elastische
Stoßwellentechnik (ISO 26203-1:2025)

This European Standard was approved by CEN on 15 November 2025.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2025 CEN All rights of exploitation in any form and by any means reserved
worldwide for CEN national Members.

Ref. No. EN ISO 26203-1:2025 E

Contents	Page
European foreword.....	3

Sample Document

get full document from standards.iteh.ai

European foreword

This document (EN ISO 26203-1:2025) has been prepared by Technical Committee ISO/TC 164 "Mechanical testing of metals" in collaboration with Technical Committee CEN/TC 459/SC 1 "Test methods for steel (other than chemical analysis)" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2026, and conflicting national standards shall be withdrawn at the latest by June 2026.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 26203-1:2018.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 26203-1:2025 has been approved by CEN as EN ISO 26203-1:2025 without any modification.

Sample Document

get full document from standards.iteh.ai



**International
Standard**

ISO 26203-1

**Metallic materials — Tensile testing
at high strain rates —**

**Part 1:
Elastic-bar-type systems**

*Matériaux métalliques — Essai de traction à vitesses de
déformation élevées —*

Partie 1: Systèmes de type à barre élastique

**Third edition
2025-12**

ISO 26203-1:2025(en)

Sample Document

get full document from standards.iteh.ai

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2025

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

© ISO 2025 – All rights reserved

ISO 26203-1:2025(en)

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and designations	1
5 Principles	3
6 Apparatus	3
7 Test piece	5
7.1 Test-piece shape, size and preparation.....	5
7.2 Typical test piece.....	7
8 Calibration of the apparatus	8
8.1 General.....	8
8.2 Displacement measuring device.....	8
9 Procedure	8
9.1 General.....	8
9.2 Mounting the test piece.....	8
9.3 Applying force.....	9
9.4 Measuring and recording.....	9
10 Evaluation of the test result	10
11 Test report	12
Annex A (informative) Quasi-static tensile testing method	13
Annex B (informative) Example of one-bar method	15
Annex C (informative) Example of split Hopkinson bar (SHB) method	22
Bibliography	29

ISO 26203-1:2025(en)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 1, *Uniaxial testing*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 459/SC 1, *Test methods for steel (other than chemical analysis)*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 26203-1:2018), which has been technically revised.

The main changes are as follows:

- modification of note in [subclause 7.1](#);
- note in [A.6](#) changed to be part of main body.

A list of all parts in the ISO 26203 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

ISO 26203-1:2025(en)

Introduction

Tensile testing of metallic sheet materials at high strain rates is important in order to achieve a reliable analysis of vehicle crashworthiness. The strain-rate range between 10^{-3} and 10^3 s⁻¹ is considered to be the most relevant to vehicle crash events based on experimental and numerical calculations such as the finite element analysis (FEA) work for crashworthiness. In order to evaluate the crashworthiness of a vehicle with accuracy, reliable stress-strain characterization of metallic materials at strain rates higher than 10^{-3} s⁻¹ is typically used. During a crash event, the maximum strain rate often reaches 10^3 s⁻¹, at which the strength of the material can be significantly higher than that under quasi-static loading conditions. Thus, the reliability of crash simulation depends on the accuracy of the input data specifying the strain-rate sensitivity of the materials.

Although there are several methods for high-strain rate testing, there are three significant problems to be solved.

The first problem is the noise in the force measurement signal.

- The test force is generally detected at a measurement point on the force measurement device that is located some distance away from the test piece.
- Furthermore, the elastic wave which has already passed the measurement point returns there by reflection at the end of the force measurement device. If the testing time is comparable to the time for wave propagation through the force measurement device, the stress-strain curve often has large oscillations as a result of the superposition of the direct and indirect waves. In quasi-static testing, contrarily, the testing time is sufficiently long to have multiple round-trips of the elastic wave. Thus, the force reaches a saturated state and equilibrates at any point of the force measurement device.

There are two different solutions for this problem.

- The first solution is to use a short force measurement device which will reach the saturated state quickly. This approach is often adopted in the servo-hydraulic type system.
- The second solution is to use a very long force measurement device which allows the completion of a test before the reflected wave returns to the measurement point. The elastic-bar-type system is based on the latter approach.

The second problem is the need for rapid and accurate measurements of displacement or test piece elongation.

- Conventional extensometers are unsuitable because of their large inertia. Non-contact type methods such as optical and laser devices should be adopted. It is also acceptable to measure displacements using the theory of elastic wave propagation in a suitably-designed apparatus, examples of which are discussed in this document.
- The displacement of the bar end is simply calculated from the same data as force measurement, i.e. the strain history at a known position on the bar. Thus, no assessment of machine stiffness is required in the elastic-bar-type system.

The last problem is the inhomogeneous section force distributed along the test piece.

- In quasi-static testing, a test piece with a long parallel section and large fillets is recommended to achieve a homogeneous uniaxial-stress state in the gauge section.
- In order to achieve a valid test with force equilibrium during the dynamic test, the test piece is designed differently from the typically designed quasi-static test piece. Dynamic test pieces are intended to be generally smaller in the dimension parallel to the loading axis than the test pieces typically used for quasi-static testing.

The elastic-bar-type system thus provides solutions for dynamic testing problems and is widely used to obtain accurate stress-strain curves at around 10^3 s⁻¹. The International Iron and Steel Institute developed the “Recommendations for Dynamic Tensile Testing of Sheet Steel” [\[1\]](#) based on the interlaboratory test

ISO 26203-1:2025(en)

conducted by various laboratories. The interlaboratory test results show the high data quality obtained by the elastic-bar-type system. The developed knowledge on the elastic-bar-type system is summarized in this document, while ISO 26203-2^[2] covers servo-hydraulic and other test systems used for high-strain-rate tensile testing.

Sample Document

get full document from standards.iteh.ai